

Technical Data Sheet

OL3300/00 AMBER-COLORED OIL FOR TEAK

DATE 12/23/14

Area of use:	New or old timber, both interior and exterior
Method of use:	Brush and wiping
Thinning:	ready to use

Technical characteristics

Solids content (%):	55 ± 2
Specific gravity (kg/l):	0.860 ± 0.030
Viscosity (DIN 2 at 20°C):	72" ± 5"

General characteristics

Drying time (50 g/m² at 20°C):	dust free	2 hrs
	touch dry	4 hrs
	recoatable	16 hrs
Spreading rate (m²/kg):	18 - 22	
Number of coats:	1 - 2	
Shelf-life (months):	Properly stored, shelf-life is unlimited.	
	After long periods of storage stir well before use	

OL3300/00 is a blend of natural oils developed for easy and quick maintenance of uncoated wooden items for exterior such as flooring, swimming pools borders, public benches, garden furniture, etc. Thanks to its formulation it provides good protection against water.

Use of product

Apply a light coat by brush then, after a minute or so, wipe with a dry cloth so as to ensure even absorption. Take care not to apply too heavy a coat. Wait one day before applying the second coat.

Special instructions

- * Do not use in rainy days or too hot weather.
- * Cloths imbued with the product may be subject to spontaneous combustion due to strong sun rays. We recommend that the cloths be soaked in water before being disposed of.
- * Clean timber carefully with a wet wipe
- * If sanding is required (in case of dirty or worn down timber), we recommend 150-180 grit sandpaper. This is also recommended for substrate preparation in case of new timber.
- * Make sure the can is well sealed in order to prevent product surface from drying.
- * Maintenance should be carried out every year or two, according to exposure conditions.

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.
 WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.