

SANDING SEALER LN-41 BLANCO

PRODUCT DESCRIPTION: White nitrocellulose primer for the sealing of wood, MDF and similar supports.

GENERAL FEATURES:

- Good covering power.
- Rapid curing.
- Great thixotropy.
- Good sandpapering.
- Good overvarnishing.
- Good adherence over the different supports.

PHYSICAL PARAMETERS (at 20°C):

- Viscosity Ford Cup N°4: 100"
- Density: 1,320 gr/cm³
- Colour:..... White.
- Solid content 57+/-1%
- Appearance in bottle: Viscous liquid.
- Appearance of dry film: White.
- Storage:..... Consume before 3 months.

DRYING TIME (100 gr/m² at 20°C):

- Dry powder: 5'
- Dry feel: 12'
- Dry sandpaper: 3 hours.
- Overvarnishing: After 8-10 hours.

| | <u>Viscosity</u> <u>application</u> | <u>Thinner</u> | <u>% de Thinner</u> |
|-------------------------------------|--|-------------------|---------------------|
| APPLICATION SYSTEMS: | | | |
| - Aerographic and airless spraying: | 30" | 200 DS or 125 DPE | 10 - 15% |
| - Electrostatic spraying: | Non | Non | Non |
| - Curtain coating: | - | - | - |
| - Roller coating: | - | - | - |
| - Immersion: | - | - | - |
| - Brush: | 100" | 200 DS or 125 DPE | - |

APPLICATION FEATURES:

- Support: All types of veneers and woods and MDF boards.
- Preparation of the support: Eliminate the residue of sandpapering.
- Paper weight: 1 - 2 coats of 130-150 gr/m².

OBSERVATIONS: Homogenize the varnish prior to use. Product recommended for lacquering small furniture (carpentries) by its easy application by brush and by spraying. Thin the product properly in every case. It is recommendable not to exceed 360 gr/m² (3 coats of 120 gr/m² each one), to avoid the effects of cracks (broken film).

REV: 0/03/2013

Instructions included in this technical data sheet and its advices have been got from our own experiences and they should be taken as guidelines, with no commitment from us. Values shown in this technical data sheet are only a reference and must not be considered as strict. The customer can and should check the goods provided by us, verifying they are right and valid for their offered purposes. It is completely out of our control the correct application of the product as well as its adequate use, variable working circumstances, etc, so this means the customer is responsible for them. This stated, we completely guarantee the quality of our products, as a consequence of our sales and delivery commitments previously established.