

LIQUID COATINGS

Technical Data Sheet

Description	: Waterborne coating based on acryl-dispersions.
Application	: As a primer and midcoat in the wood processing industry
Specific Properties	: Good flow, adhesion and elasticity properties. A fast low water uptake. Fast drying. Isolating properties on various wood species. For interior and exterior use.

Technical Specifications

Product number	: PE 025QO
Degree of gloss	: mat
Colour Assortment	: white
Solid Content	: approx. 52 gew.% = approx. 40 vol.%
Density	: approx. 1,3 kg/dm ³ at 20°C
Drying times (20°C/65% RV)	: dust dry : after approx. 30 minutes
at a wet film thickness of 175 µm	: manageable : after approx. 2 hours
	: through dry : after approx. 72 hours
Recoatibility	: after min. : 4 hours
	: after Max. : not limited
Flashpoint (DIN 53213)	: non flammable

Processing Specification

Ambient conditions	: Temperature between 15 and 25°C
	: RH between 40 and 70%
Thinner	: to change viscosity : Water
	: for cleaning the equipment : Water
Forced drying	: approx. 60 min. at 30°C
Advised film thickness per coat	: dry film thickness: 70 µm = wet film thickness: 175 µm
Theoretical yield	: approx. 5,7 m ² /lt at 70 µm dry film thickness
Practical yield	: The practical yield depends on the way of application the quality of the substrate and the shape of the object.
Specials details	: Stirr well before use.



PPG Logo is a registered trademark and "We protect and beautify the world" is a trademark of PPG Industries Ohio, Inc



We protect and
beautify the world™

Wood Finishes

PE 025QO white

LIQUID COATINGS

Technical Data Sheet

Application Information

APPLICATION METHODS	Pressure	Nozzle-size	guide-air	Max.temp. Coating	Remarks
Pneumatic spraying	3-4 bar	1,8-2,2 mm			add max. 10% water
Airless/Airmix spraying	60-120 bar	0,013-0,015 inch	max. 2 bar	30°C.	add max. 5% water.
Electrostatic spraying	not relevant				
Rollercoater	not relevant				
Curtaincoater	not relevant				
Vacuümcoaten	not relevant				
Dipping	not relevant				
Flowcoater	not relevant				
Brush-Roller	not relevant				

Substrate Information

Substrate conditions	As a minimum for the construction follow the guidelines of BS 644			
Suitable wooden substrates	Spruce	Scots pine	Meranti	Plywood
	Mahogany	Larch	Douglas fir	Idigbo
	Sapele	Eucalyptys grandis	MDF	Oak
Other surfaces	Accoya	Tricoya	Woodstone	Rockpanel
Note	The moisture content of the wood should be between 12-16%.			
Demands	The substrate to be treated should be free of (sanding)dust, grease or other contaminations.			



PPG Logo is a registered trademark and "We protect and beautify the world" is a trademark of PPG Industries Ohio, Inc

LIQUID COATINGS

Technical Data Sheet

Further Information

Shelf life : If stored in original packaging in cool and frost-free areas, approx. 18 months.

Safety Information For exact information see the safety data sheet.

Environment : Storage, use and waste disposal in accordance with local legislation. May not be disposed into sewerage.

Systems For possible paint systems please contact Movac .

The technical data presented in this bulletin is based upon information believed by PPG to be currently accurate. However, no guarantees of accuracy, comprehensiveness, or performance are given or implied. Continuous improvements in coatings technology may cause future technical data to vary from what is in this bulletin. Contact your PPG representative for the most up-to-date information.

PPG Industrial Coatings B.V.
Duiven, NETHERLANDS
Tel. : +31 316 700 150
Email: industrial-coatings-emea@ppg.com

PPG Polifarb Cieszyn S.A.
Cieszyn, POLAND
Tel.: +48 33 851 71 00
Fax: +48 33 852 24 93

PPG WEB SITES: www.ppg.com & www.ppgindustrialcoatings.com



PPG Logo is a registered trademark and "We protect and beautify the world" is a trademark of PPG Industries Ohio, Inc