

COMPANY WITH MANAGEMENT SYSTEM - UNI EN ISO 9001 -- UNI EN ISO 14001 - Sherwin-Williams Italy S.r.I. – con unico socio Via del Fiffo, 12 - 40065 Pianoro (BO) - Italia - C.P. 18 tel. +39 051 770 511 - fax +39 051 777 437 www.sayerlack.com Cod. Fisc. e Reg. Impr. Bo 08866930152 P. IVA: IT 00494251200 - R.E.A. n. 313180 Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531

Company under the direction and coordination of The Sherwin-Williams Company, USA

Technical Data Sheet

OL3100/00 NATURAL-LOOK IMPREGNATING OIL FOR EXTRUDER

DATE 12/22/14

Area of use:	panels, frames and skirting boards
Method of use:	Extruder, spray, brush and wiping
Thinning:	ready to use

Technical characteristics

Solids content (%):	24 ± 1
Specific gravity (kg/l):	0.800 ± 0.030
Viscosity (DIN 2 at 20°C):	52" ± 5"

General characteristics

Recommended application weight (gr/m ²):	from 30 to 80
Drying time (50 g/m ² at 20°C):	dust free 30'
	touch dry 60'
Number of coats:	1-2
Shelf-life (months):	If the product is properly stored, shelf-life is unlimited.
	After long periods of storage, always check homogeneity and stir well before use to eliminate any possible sediment.

OL3100/00 is a blend of special oils and selected waxes studied for an easy and quick application.

It enables impermeabilization and preservation of wooden items while maintaining the original natural-wood appearance.

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

NAW WELL ALL WORKING CONVOLUTING. WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.