

LIQUID COATINGS

Technical Data Sheet

Description	: Waterborne coating based on alkyd-emulsion.
Application	: As a impregnation in the wood processing industry
Specific Properties	: Has an active function against fungus. Improves adhesion properties of the paintsystem and harmonized the uptake of stain or primer. Little roughening of the wood fiber. Suitable for class 3 of the BS/EN 335-1 such as windows and doors. Only suitable for exterior use when over coated

Technical Specifications

Product number	: CE 120QT
Degree of gloss	: not relevant
Colour Assortment	: colourless
Solid Content	: approx. 8 gew.% = approx. 8 vol.%
Density	: approx. 1,01 kg/dm ³ at 20°C
Drying times (20°C/65% RV)	: dust dry : after approx. 2 hours
at a wet filmthickness of 50 µm	: manageable : after approx. 3 hours
	: through dry : after approx. 72 hours
Recoatibility	: after min. : 6 hours
	: after Max. : 4 weeks
Flashpoint (DIN 53213)	: non flammable

Processing Specification

Ambient conditions	: Temperature between 15 and 25°C
	: RH between 40 and 70%
Thinner	: to change viscosity : Water
	: for cleaning the equipment : Water
Forced drying	: not relevant
Advised filmthickness per coat	: dry filmthickness: 4 µm = wet filmthickness: 50 µm
Theoretical yield	: approx. 20 m ² /lt at 4 µm dry filmthickness
Practical yield	: The practical yield depends on the way of application the quality of the substrate and the shape of the object.
Specials details	: Stirr well before use.
	: Biocide products must be handled carefully
	: Before use, read the identification and product information.
	: Undiluted using.



PPG Logo is a registered trademark and "We protect and beautify the world" is a trademark of PPG Industries Ohio, Inc



We protect and
beautify the world™

Wood Finishes

CE 120QT

LIQUID COATINGS

Technical Data Sheet

Application Information

APPLICATION METHODS	Pressure	Nozzle-size	guide-air	Max.temp. Coating	Remarks
Pneumatic spraying	not relevant				
Airless/Airmix spraying	not relevant				
Electrostatic spraying					
Rollercoater	not relevant				
Curtaincoater	not relevant				
Vacuümcoaten	not relevant				
Dipping	The product is ready for use				
Flowcoater	The product is ready for use				
Brush-Roller	The product is ready-to-use.				

Substrate Information

Substrate conditions	As a minimum for the construction follow the guidelines of BS 644			
Suitable wooden substrates	Spruce	Scots pine	Larch	Douglas fir
Other surfaces				
Note	The moisture content of the wood should be between 12-16%.			
Demands	The substrate to be treated should be free of (sanding)dust, grease or other contaminations.			



PPG Logo is a registered trademark and "We protect and beautify the world" is a trademark of PPG Industries Ohio, Inc



We protect and
beautify the world™

Wood Finishes

CE 120QT

LIQUID COATINGS

Technical Data Sheet

Further Information

Shelf life : If stored in original packaging in cool and frost-free areas, approx. 18 months.

Safety Information For exact information see the safety data sheet.

Environment : Storage, use and waste disposal in accordance with local legislation. May not be disposed into sewerage.

Systems For possible paint systems please contact Movac .

The technical data presented in this bulletin is based upon information believed by PPG to be currently accurate. However, no guarantees of accuracy, comprehensiveness, or performance are given or implied. Continuous improvements in coatings technology may cause future technical data to vary from what is in this bulletin. Contact your PPG representative for the most up-to-date information.

PPG Industrial Coatings B.V.
Duiven, NETHERLANDS
Tel. : +31 316 700 150
Email: industrial-coatings-emea@ppg.com

PPG Polifarb Cieszyn S.A.
Cieszyn, POLAND
Tel.: +48 33 851 71 00
Fax: +48 33 852 24 93

PPG WEB SITES: www.ppg.com & www.ppgindustrialcoatings.com



PPG Logo is a registered trademark and "We protect and beautify the world" is a trademark of PPG Industries Ohio, Inc