

Sayerlack is a brand of
SHERWIN-WILLIAMS

SAYERLACK S.r.l. - With a Single Shareholder

Via del Fiffò, 12 - 40065 Pianoro (BO) - Italia - C.P. 18
tel. +39 051 770511 - fax +39 051 777437
www.sayerlack.it - www.lineablavernici.it

Cod. Fisc. e Reg. Impr. Bo 08866930152 - P. IVA: IT 00494251200

R.E.A. n. 313180 - Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531

Company under the direction and coordination of The Sherwin-Williams Company, USA

Technical Data Sheet

DP0705/00 REACTIVE THINNER FOR POLYESTERS

DATE 16/10/00

Technical characteristics:

Specific gravity (kg/l):	0.890 ± 0.030
Flash point:	+32 °C
Shelf-life (months):	6

General characteristics

DP0705/00 is a specific thinner for polyester basecoats and topcoats both air-drying or UV curing.

It is called "reactive" because, instead of evaporating and escaping from the coatings film as the conventional thinners do, it reacts with the resin and contributes to the film formation. However, DP0705/00 slows down drying and it should be used in small percentages and only when a slower drying is required, for example to obtain a better flow.

Warning

As shown by the shelf-life of 6 months, DP0705/00 is a thinner which deteriorates easily.

It is to be kept in fresh areas and once the package has been opened, the product has to be consumed in a short time. Deterioration shows at the beginning with a veiled look, followed then by solidification.

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.