

COMPANY WITH
MANAGEMENT SYSTEM
- UNI EN ISO 9001 - UNI EN ISO 14001 -

Sherwin-Williams Italy S.r.l. – con unico socio Via del Fiffo, 12 - 40065 Pianoro (BO) - Italia - C.P. 18 tel. +39 051 770 511 - fax +39 051 777 437 www.sayerlack.com Cod. Fisc. e Reg. Impr. Bo 08866930152 P. IVA: IT 00494251200 - R.E.A. n. 313180 Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531

Company under the direction and coordination of The Sherwin-Williams Company, USA

Technical Data Sheet

OL3000/00 OIL FOR WOOD TREATMENT

DATE 12/22/14

Area of use:	Various supports and parquet
Method of use:	Spray, brush and wiping, roller
Thinning:	ready to use (dilutable 10-30%)

Technical characteristics

Solids content (%):	52 ± 1
Specific gravity (kg/l):	0.93 ± 0.030
Viscosity (DIN 4 at 20°C):	150" ± 10"

General characteristics

Recommended application weight (gr/m²):	from 30 to 80
Drying time (50 g/m² at 20°C):	stackable 24 - 36h
Number of coats:	2-more
Shelf-life (months):	12 month
	After long periods of storage, always check homogeneity and stir well before use to eliminate any possible sediment.

We recommend to stir the product before application.

OL3000/00 is an urethane oil expecially developed for parquet application.

We suggest to apply at least 2 coats of oil to obtain better chemical and mechanical resistance.

To achive the best wood wetting we suggest to dilute the first coat with 10%-30% (depending on the application) of a thinner as DE0703/00.

After the application of the oil we suggest to remove the excess of product by using a wipe. It's possible anyway not to brush the last layer of oil to achive better resistance. Remember to wash the used wipe with water before trashing them. They are subject to self-ignition.

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.