



MOVAC

PRODUCT TECHNICAL INFORMATION SHEET

!HNPVCWF* PVC LACQUERS AND PAINTS

DESCRIPTION	Water based lacquers and paints for use on Flexible PVC																										
AREAS OF USE	Most surfaces composed of PVC.																										
PRODUCT CHARACTERISTICS	<p>Good clarity (clear lacquer only)</p> <p>Good flexibility</p> <p>Good build</p>																										
METHODS OF APPLICATION AND USE OF PRODUCT	<p>By brush and all spray types provided they are suitable for contact with water.</p> <p>Application and drying should be carried out in temperatures above 15°C and relative humidity below 85% or the curing of the film and final durability will be impaired.</p>																										
MIXING PROCEDURE	Ready for use. May be thinned with tap water.																										
DATA	<table border="0"> <tr> <td>Solid content (% w/w)</td> <td>30-40 depending on colour</td> </tr> <tr> <td>Density (Kg/L)</td> <td>1.001-1.2 depending on colour</td> </tr> <tr> <td>Viscosity (Brookfield, spindle 2 speed 20 @ 20°C)</td> <td>300cps</td> </tr> <tr> <td>Recommended film weight (g/m2)</td> <td>50-100</td> </tr> <tr> <td>Recommended maximum number of coats</td> <td>2</td> </tr> <tr> <td rowspan="4">Drying time (100 g/m2 @ 20°C)</td> <td>Dust free</td> <td>30 mins.</td> </tr> <tr> <td>Touch dry</td> <td>60 mins.</td> </tr> <tr> <td>Overcoatable</td> <td>4 hours</td> </tr> <tr> <td>Stackable</td> <td>24 hours</td> </tr> <tr> <td rowspan="3">Forced drying</td> <td>Flash off</td> <td>15 mins.</td> </tr> <tr> <td>Hot air 35°C</td> <td>45 mins.</td> </tr> <tr> <td>Cooling</td> <td>15 mins.</td> </tr> </table>	Solid content (% w/w)	30-40 depending on colour	Density (Kg/L)	1.001-1.2 depending on colour	Viscosity (Brookfield, spindle 2 speed 20 @ 20°C)	300cps	Recommended film weight (g/m2)	50-100	Recommended maximum number of coats	2	Drying time (100 g/m2 @ 20°C)	Dust free	30 mins.	Touch dry	60 mins.	Overcoatable	4 hours	Stackable	24 hours	Forced drying	Flash off	15 mins.	Hot air 35°C	45 mins.	Cooling	15 mins.
Solid content (% w/w)	30-40 depending on colour																										
Density (Kg/L)	1.001-1.2 depending on colour																										
Viscosity (Brookfield, spindle 2 speed 20 @ 20°C)	300cps																										
Recommended film weight (g/m2)	50-100																										
Recommended maximum number of coats	2																										
Drying time (100 g/m2 @ 20°C)	Dust free	30 mins.																									
	Touch dry	60 mins.																									
	Overcoatable	4 hours																									
	Stackable	24 hours																									
Forced drying	Flash off	15 mins.																									
	Hot air 35°C	45 mins.																									
	Cooling	15 mins.																									
STORAGE	<p>Must be stored in temperatures above 5°C.</p> <p>Shelf life 12 months.</p>																										
FURTHER INFORMATION	<p>Read the separate Health and Safety sheet prior to use.</p> <p>This is just one of a wide range of industrial coatings from Movac Group Ltd. Should you require any further information on this, or any other product within our range, simply contact us at the address below.</p>																										