

TECHNICAL DATA SHEET

supersedes previous issue dated 01/02/04

SU 700
CLEAR NITROCELLULOSE BASECOAT

Area of use:	General purpose	
Method of use:	by spray (conventional, airmix or electrostatic) or by curtain coater.	
Mixing procedure:	by weight	
	SU 700	100
	DT 436	20

Technical characteristics

Solids content (%):	28 ± 2
Specific gravity (kg/l):	0.960 ± 0.030
Viscosity (DIN 4 at 20°C):	36" ± 2"

Substrate preparation

With solvent-based stains, if tinting is desired.

General characteristics

Recommended application weight (g/m ²):	approx. 120	
Drying time (100 g/m ² at 20°C):	dust free	10'-12'
	touch dry	30'
	through dry	90'
Shelf-life:	If the product is properly stored, shelf-life is unlimited. After long periods of storage, always check homogeneity and stir well before use to eliminate any possible sediment.	

SU 700 is nitrocellulose basecoat characterised by a high surface hardness and high solids contents.

It ensures good sandability and, thanks to its thixotropy, it is suitable also for vertical applications.