

supersedes previous issue dated 06/02/06

TZ 90**

CLEAR POLYURETHANE TOPCOAT - HIGH SCRATCH AND ABRASION RESISTANCE

Versions:	10, 20, 30, and 40 gloss		
Area of use:	Flat parts of furniture, doors, tables, panels, office furniture		
Method of use:	Curtain coater, spray gun		
Mixing procedure:		by weight (kg)	
	Part A:	TZ 90**	100
	Part B (hardener):	TH 759	50
	Thinner:	DT 90	20-40

Technical characteristics

Solids content (%):	41 ± 2
Specific gravity (kg/l):	1.030 ± 0.030
Viscosity (DIN 4 at 20°C):	70"± 5"

Substrate preparation

With polyurethane or polyester basecoats and UV fillers .

General characteristics

Pot-life at 20°C:	2 hours		
Recommended application weight (g/m²):	min. 80 - max. 150		
Drying time (100 g/m² at 20°C):	dust free	10'	
	touch dry	30'	
	stackable	3 hours	
Forced air drying: (100 g/m²):	flash-off	10'	
	hot air at 50°C	40'-60'	
	cooling	10'	
Shelf-life:	If the product is properly stored, shelf-life is unlimited. After long periods of storage, always check homogeneity and stir well before use to eliminate any possible sediment.		

TZ90** is a clear polyurethane topcoat ensuring an extremely high scratch and abrasion resistance, as well as a fast drying. Particularly suitable for office furniture.

We advise against its use with high pressure airless systems.

Warning

In order to obtain always the same gloss level, we recommend to always stir thoroughly part A using a spatula.

When a light tinting is required, use XC1900/XX concentrated stains.