

TECHNICAL DATA SHEET

VS5342/00
WATERBORNE SOFT-FEEL TOPCOAT FOR INTERIORS

Versions:	0 gloss		
Area of use:	doors, furniture parts, metal and plastic componentes		
Method of use:	airmix, airless, conventional, electrostatic spray gun, provided that equipment is suitable for use with waterborne products		
		by weight (kg) by volume (l)	
Part A:	VS5342/00	100	100
Part B (hardener):	AH1550/00	10	10

Technical characteristics

Solids content (%):	31 ± 2
Specific gravity (kg/l):	1.020 ± 0.030
Viscosity (DIN 4 at 20°C):	60" ± 5"

General characteristics

Pot life at 20°C:	8 hours
Recommended application weight (g/m ²):	min. 70 - max. 130
Number of coats:	1
Drying time (120 g/m ² at 20°C):	touch dry 2 hours through dry 8 hours stackable 24 hours
	10 m ² /l 15

VS5342/00 is a 2-pack acrylic-polyurethane waterborne topcoat designed to achieve a 0-gloss soft-feel effect. Thanks to its special formulation, it allows good adhesion on waterborne basecoats and on substrates other than wood, such as metal and plastics.

Substrate preparation

With one or more coats of Hydroplus waterborne or polyester basecoat, suitably dried and sanded.

Application

By spray (airless, airmix or conventional) both horizontally and vertically.

We advise against using very thick layers of topcoat in a single application since uneven drying of the film can give rise to cracking, especially in areas of build up (grooves in shaped panels).

Following are some guidelines:

1. Conventional spray: 1.9 mm nozzle, pressure: 3-4 bar
2. Airmix: 11 mm nozzle, pressure of coating: 80-100 bar; air pressure: 1-2 bar 3.
- Airless: 11 mm nozzle, pressure of coating: 150-200 bar
4. The use of a pre-atomizer and/or of a pre-heater (30-35°C) has given excellent results in terms of flow and quality consistency.

If application devices are not in perfect conditions (defective gaskets, too high pressure, etc.) they may cause major defects in the coatings film (e.g. air bubbles).

We recommend the use of 2-head pumps in order to reduce waste and to improve the quality of the coating applied in terms of resistance to stacking and to chemicals.

TECHNICAL DATA SHEET

VS5342/00

WATERBORNE SOFT-FEEL TOPCOAT FOR INTERIORS

Drying

2-pack waterborne products must be dried in rooms with temperatures no lower than 15°C and relative humidity no greater than 70%. Outside this range drying is slower and/or the film is formed with poorer hardness and chemical resistance. For good drying it is advisable to use a forced flow of dry air initially at room temperature and subsequently at 35°C.

Warning

- Do not store the product at temperatures lower than 5°C or higher than 35°C.. • Coating residues must be disposed of in accordance with current legislation. Do not pour residues down drains.
- In view of the wide variety of materials used for manufacturing wooden products, when switching from a solvent-based to a waterborne coating system it is always advisable to contact your suppliers' technical departments to check whether your equipment and components are. In particular, check: electrostatic guns, pumps, seals, silicones, glues, booth treatment water products and packaging materials.
- Once the can has been opened, the waterborne protective wood stay may rot because of the attack of bacteria, moulds and fungi commonly present in the air. This phenomenon is easily detectable because of the bad smell, increase of viscosity, mould on the surface and change of color. This problem may take place also in case of products left for a long time in vessels for dipping or flow-coating application, mainly during summertime. The use of drinking water, a frequent cleaning of the plant (possibly with disinfectant solutions) and the periodic addition of XA 4051 bactericide (0.1-0.2%) increase preservation of the products used. As a disinfectant use a 2% solution in water of XA 4051. As to application method relating to XA 4051, please refer to its technical data sheet.

N.B.: Data provided on this Technical Data Sheet correspond to our best knowledge and experience. We assure consistency on the chemical-physical characteristics of our products, within the tolerance limits specified on our Technical Data Sheets. Responsibility of final result of product application is fully up to the users, who shall make sure that the product corresponds to their own needs with regard to application system, to substrates used as well as to working conditions.

WARNING: Actual viscosity of some pigmented and/or thixotropic products may differ from the viscosity shown on the Technical Data Sheet. Differences are to be regarded as acceptable if within 30% maximum.