

sikkens

Transparent

Factory Applied

KODRIN WV456

Coatings

Transparent sealer for application to exposed end grain of primed or base stained joinery.

- Quick drying and recoat time
- Good adhesion to base stained or primed timber
- Easy to use
- Single pack

Composition
Polyacrylic resin.

Drying Times
Recoat time is approximately 1 hour at 23°C and 50% relative humidity. The product must have become transparent before overcoating.

Notes
Kodrin WV 456 must be recoated before being exposed externally.

Flash Point
>100°C

Volume Solids
Approximately 29%

Method
For end grain sealing, use a small stiff bristle brush, or small filling knife. Apply to saturation on end grains, to primed or base stained timber.

Viscosity
Thixotropic Paste

Cleaning
Clean equipment immediately after use with a solution of Sikkens ST830 and fresh luke warm water.

Colour Range
Colourless only

Pack Size
750ml plastic container

Storage
Store in a cool but frost free area.

Recommended Recoating
Can be recoated with all Sikkens Joinery midcoats and finishes.

KODRIN WV456



KODRIN 456

It is our recommendation that all windows, doors, etc. should receive at least one coat of base stain or primer and one midcoat in the joinery factory prior to arrival on site. We would recommend you always seek exact system advice from our Customer Support Centre or one of our Joinery Account Managers.

Before using this product please read the Material Safety Data Sheet for Sikkens Kodrin WV 456. If you do not understand any part of this Technical Data Sheet, or the Material Safety Data Sheet, please contact the **Customer Support Centre** on **01480 496868**.

This data sheet supersedes all previous data sheets supplied relating to this product. It contains important information which must be communicated to the user. Users must satisfy themselves of the suitability of the product for the intended application and surface, as surface and application conditions are beyond the control of Akzo Nobel Woodcare. Users must also satisfy themselves of the suitability of the product in circumstances other than those set out in this data sheet. Akzo Nobel Woodcare is always willing to answer user's enquiries regarding its products.

For further help and information on recommended coating systems and specifications please contact the **Customer Support Centre** on **01480 496868**.

The information above is correct at the date of issue 1/4/2002.

Product Code: 4ABXJ22600



Akzo Nobel Woodcare
Meadow Lane, St Ives, Cambridgeshire PE27 4UY

Tel: 01480 496868 Fax: 01480 496801 E-mail: sikkens@sis.akzonobel.com
www.sikkens.co.uk

Akzo Nobel Woodcare is a trading division of Akzo Nobel Decorative Coatings Limited.