

WZ 5300 FAST DRY AC TOPCOATS

PRODUCT DESCRIPTION

Clear acid catalysed lacquers available in a variety of gloss levels.

AREAS OF USE

A high build AC lacquer for furniture and all wooden substrates for internal use.

PRODUCT CHARACTERISTICS

- Fast drying
- Good build
- Low formaldehyde emissions
- Low VOC's

METHODS OF APPLICATION AND USE OF PRODUCT

Conventional, airmix and airless spray.

MIXING PROCEDURE

	Parts by Volume
WZ5340	90
WH 751 Catalyst	10
Thin as necessary to achieve the required viscosity with DSG 27 AC thinners	

DATA

Solids (% w/w)	37	
Density (kg/L)	0.94	
VOC (g/L)	592	
Solids (g/L)	348	
Viscosity (Ford 4 @ 20°C)	25 Sec ±1	
Recommended film weight (g/m ²)	100-150	
Number of coats	2 max	
Drying times (100g/m ² @ 20°C)	Dust free Touch dry	5-10 mins. 30 mins
Stackable	6 hours	
Forced air ventilation (100g/m ²)	Flash off Time at 50°C Cooling	20 mins 40 mins 20 mins

STORAGE

12 months in sealed containers. Store at temperatures above 15 °C.

FURTHER INFORMATION

Read the separate Health and Safety sheet prior to use.

This is just one of a wide range of industrial wood coatings from Arch. Should you require any further information on this, or any other product within our range, simply contact us at the address below.