

Sayerlack is a brand of
The Sherwin-Williams Company

SAYERLACK S.r.l. - Con Unico Socio

Via del Fiffò, 12 - 40065 Pianoro (BO) - Italia - C.P. 18
tel. +39 051 770511 - fax +39 051 777437
www.sayerlack.it - www.lineablavernici.itCod. Fisc. e Reg. Impr. Bo 08866930152 - P. IVA: IT 00494251200
R.E.A. n. 313180 - Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531
Società soggetta a direzione e coordinamento di The Sherwin-Williams Company, USA

TECHNICAL DATA SHEET

IFS2984/36**CHROME SILVER EFFECT**

Colour:	Silver
Area of use:	Picture frames, furniture
Method of use:	Spray (with half-closed gun)

Technical characteristics

Solids content (%):	11 ± 2
Specific gravity (kg/l):	0.920 ± 0.030
Viscosity (DIN 4 at 20°C):	12 ± 1

Substrate preparation

Polyurethane or polyester basecoats properly sanded. Then apply the PU highgloss topcoat TL0335/A5 or TL0336/00 pigmented with 20% of paste TP3300/22.

Wait 24 hours and then apply IFS2984/36; after 24 hours fix the silver effect by applying AF7290/00 or SZ4190/00.

Subsequently, it can be overcoated with PU topcoats (for coating systems without AF7290/00 only).

Special instructions

Shelf-life is 6 months. Always check homogeneity and stir well before use to eliminate any possible sediment.