

## Technical Data Sheet

## XAL3326/XX ASTRAL: GLITTER PIGMENTS FOR SPECIAL EFFECTS

DATE 01/29/2014

These special effect pigments are composed of particles with a metallic shine especially bright and colorful. They can be used both on solventborne and waterborne systems.

Versions:	XAL3326/73 silver XAL3326/35 gold XAL3326/34 gold holographic multicolor
Area of use:	Sparkling Special Effects
Method of use:	Conventional spray
Mixing procedure ( by weight ):	0,5 – 1,0% under mechanical stirring

### Technical characteristics

Solids content (%):	100%, all.
Specific gravity (kg/l):	XAL3326/73. 1,40±0,03 Bulk density 0,45±0,05 XAL3326/35. 1,40±0,03 Bulk density 0,45±0,05 XAL3326/34. 1,50±0,03 Bulk density 0,40±0,10
Appearance	Sparkling dust
Shelf life ( months )	24

### GLASS PAINTING

The cycle is composed of two coats:

- The first is the transparent converter AV1940/00 containing about 0,1 – 1,0 of Astral- glitters. To be used within one week.
- The second coat is a covering lacquer, i.e. the WB topcoat for glass based on AT9930/NN + tinting pastes XA2006/XX.

### WOOD PAINTING

The support must be previously prepared with a suitable PU or PE sanded primer of the desired color.

The cycle is composed of two coats:

- The first is the transparent converter IFL3336/NN containing about 0,1 – 1,0 of Astral- glitters. To be used within one week.
- The second is a clear, high gloss, acrylic topcoat, i.e. TL0339/00. Better if two coats with intermediate sanding.

You can combine different colors of glitter and lacquer in order to realize a wide range of results.

COMPANY WITH  
MANAGEMENT SYSTEM  
- UNI EN ISO 9001 -  
- UNI EN ISO 14001 -

Sherwin-Williams Italy S.r.l. – con unico socio  
Via del Fiffo, 12 - 40065 Pianoro (BO) - Italia - C.P. 18  
tel. +39 051 770 511 - fax +39 051 777 437  
www.sayerlack.com  
Cod. Fisc. e Reg. Impr. Bo 08866930152  
P. IVA: IT 00494251200 - R.E.A. n. 313180  
Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531

Company under the direction and coordination of The Sherwin-Williams Company, USA

### General guidelines

Astral Glitters must be added to the transparent converter before the use, better if added by mechanical stirring in order to avoid the formation of lumps.

Once prepared the product must be used within one week in order to avoid pigment discoloration.

Store tightly closed in its original container, at temperature between +5°C - +35°C.

**N.B.:** DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

**WARNING:** ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.