

Technical Data Sheet

XP0566/00 WATER-REPELLENT WAX FOR FURNITURE

Supersedes previous issue dated 11.12.14

DATE 09/30/16

Area of use:	Panelling, furniture
Method of use:	Brush, wiping, spray gun.
Thinning:	Ready to use.

Technical characteristics:

Solids content (%):	13 ± 1
Viscosity (DIN 2 at 20°C):	49" ± 5"
Specific gravity (kg/l):	0.796 ± 0.030
Drying time (100 g/m ² at 20°C):	Touch dry: 12 hours
Shelf-life:	If the product is properly stored, shelf-life is unlimited. After long periods of storage, always check homogeneity and stir well before use to eliminate any possible sediment.
Shelf-life (months):	36 in the original package

General characteristics

This synthetic water-repellent wax is designed for treatment of veneer or solid wood parts requiring a natural, untreated look, but with a soft touch.

XP0566/00 can be applied by spray gun, brush or wiping. Once dry it forms a very thin layer, leaving the treated piece with a natural look but a very soft and smooth touch. The product also has very good water-repellency and good stain resistance. To increase the product's level of protection and smoothness, a second coat of XP0566/00 can be applied 24 hours after the first. XP0566/00 is not suitable for exterior exposure since it provides no protection against either blue staining fungi or degradation caused by UV radiation.

If thinning is required, use thinner DE0703/00.

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.