

Technical Data Sheet**IFS2984/36
CHROME SILVER EFFECT**

DATE 04/05/09

Colour:	Silver
Area of use:	Picture frames, furniture
Method of use:	Spray (with half-closed gun)

Technical characteristics

Solids content (%):	11 ± 2
Specific gravity (kg/l):	0.920 ± 0.030
Viscosity (DIN 4 at 20°C):	12 ± 1

Substrate preparation

Polyurethane or polyester basecoats properly sanded. Then apply the PU highgloss topcoat TL0335/A5 or TL0336/00 pigmented with 20% of paste TP3300/22.

Wait 24 hours and then apply IFS2984/36; after 24 hours fix the silver effect by applying AF7290/00 or SZ4190/00.

Subsequently, it can be overcoated with PU topcoats (for coating systems without AF7290/00 only).

Special instructions

Shelf-life is 6 months. Always check homogeneity and stir well before use to eliminate any possible sediment.

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.