

Sayerlack is a brand of
The Sherwin-Williams Company

SAYERLACK S.r.l. - Con Unico Socio

Via del Fiffio, 12 - 40065 Pianoro (BO) - Italia - C.P. 18
tel. +39 051 770511 - fax +39 051 777437
www.sayerlack.it - www.lineablavernici.itCod. Fisc. e Reg. Impr. Bo 08866930152 - P. IVA: IT 00494251200
R.E.A. n. 313180 - Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531
Società soggetta a direzione e coordinamento di The Sherwin-Williams Company, USA

TECHNICAL DATA SHEET

XA4016/00**SLOW EVAPORATING THINNER FOR WATERBORNE COATINGS**

Technical characteristics

Dosage:	from 1 to 4%
Specific gravity (kg/lt):	1.030 ± 0.030
Shelf-life:	If the product is properly stored, shelf-life is unlimited. After long periods of storage, always check homogeneity and stir well before use.

General characteristics

XA4016/00 is a blend of glycols to be used to the following purposes:

- increase wettability of topcoats, particularly during summertime or in tropical areas;
- increase flow of protective wood stains, both applied by brush or by flow-coating;
- slow down drying of waterborne coatings, increasing dust-free time.

XA4016/00 is conceptually different from XA4017/00: the former slows down drying while the latter restores the volatile compounds evaporated from the protective wood stains during application.

Directions of use

New protective wood stain	Add from 1% to 3% only once to the fresh product in summertime or in tropical areas in order to slow down drying and improve flow. Excellent results in brush applications.
Recovered protective wood stain	Add from to the recovered product if drying is to be slowed down and only if it was not added to the fresh product. Details as described for addition the fresh product.
New topcoat	In the hottest days during summertime or in tropical areas, particularly on robot equipment, add only once from 1% to 2% in order to improve wettability and decrease topcoat drying speed. This quantity is not to be deducted from the thinning water. Excellent results also with rotating guns.
Recovered topcoat	Add to the recovered product if drying is to be slowed down and only if it was not added to the fresh product. Details as described for addition the fresh product.