

Technical Data Sheet

XM7100/XX LIGHT FAST SOLVENT-BASED HARMONISING STAINS

Supersedes previous issue dated 07.23.14

DATE 11/20/14

Colours available:	04 yellow 13 white 14 dark blue 25 flame red 26 bright red 72 black 87 antique walnut 90 mahogany
Area of use:	Flat parts, turned parts, kitchen doors, profiles.
Method of use:	Spray

Technical characteristics:

Solids content (%):	XM7100/XX	11 ± 1
	XM7100/13	22 ± 1
Specific gravity (kg/l):	XM7100/XX	0.870 ± 0.030
	XM7100/13	0.975 ± 0.030
Light fastness:	Excellent for interior use.	
Shelf-life:	If the product is properly stored, shelf-life is unlimited. After long periods of storage, always check homogeneity and stir well before use to eliminate any possible sediment.	
Shelf-life (months):	15 in the original package	

General characteristics

XM7100/XX are solvent based wood stains for spray application.

On application, they have to be thinned down with DX0986/00 or DS1105/00 (1:2 to 1:10, depending on the desired intensity of the stain).

Use as pastel stain

XM7100/XX can be used to obtain pastel colours by mixing XM7100/13 (white) with the other colours. Such pastel colours can be thinned with DT1150/00 or DT1146/00 in a ratio from 1:3 to 1:5.

Warning

Stir the product in the can before use to disperse sedimentation.

Too heavy coats, particularly of the white, may cause adhesion problems. Avoid product build-up and check the product adhesion to substrate.

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.