

Technical Data Sheet

WU0237/13
ACID-CURE BASECOAT WHITE 2-PACK
Supersedes previous issue dated 02.01.17

DATE 02/16/17

Method of use:	Spray
Mixing procedure:	By weight (kg)
	WU0237/13 100
	WH0750/00 10
	DT0436/00 20-30

Technical characteristics:

Solids content (%):	65 ± 2
Specific gravity (kg/l):	1.360 ± 0.030
Brookfield viscosity (cps – probe 3, 20 rpm at 20°C):	3500 ± 250
Pot life:	36-48 hours

Substrate preparation

Thorough sanding and subsequent cleaning of the bare wood.

General characteristics

Recommended application weight (g/m²):	120 – 150 per coat
Drying time (100 g/m² at 20°C):	Dust free: 10' Touch dry: 30' Stackable: 3 hours
Shelf-life (months):	12 After long periods of storage, always check homogeneity and stir well before use to eliminate any possible sediment.

WU0237/13 is an acid-cure basecoat which exhibits excellent hiding power coupled with very easy sanding.