

## SANDING SEALER LN-119

**PRODUCT DESCRIPTION:** Transparent nitrocellulose primer for the sealing of wood.

**GENERAL FEATURES:**

- Great covering power.
- When conveniently diluted, suitable for application by any kind of spraying guns.
- Excellent wetting and very good smoothness.
- Rapid curing.
- Easy hand sanding with 280-320 grains.
- Good behavior in moist atmospheres.

**PHYSICAL PARAMETERS ( at 20° C):**

- Viscosity Ford Cup N° 4: ..... 100"
- Density: ..... 0,945 gr/cm<sup>3</sup>
- Solid %: ..... 31%.
- Colour: ..... Honey color.
- Appearance in bottle: ..... Viscous liquid.
- Appearance of dry film: ..... Colourless.
- Storage: ..... 12 months.

**DRYING TIME (100 gr/m<sup>2</sup> at 20° C):**

- Dry powder: ..... 5'
- Dry feel: ..... 13'
- Dry sandpaper: ..... 2 -3 hours.
- Overvarnishing: ..... Over 4-6 hours.

	<u>Viscosity application</u>	<u>Thinner</u>	<u>% Thinner</u>
<b>APPLICATION SYSTEMS:</b>			
- Aerographic and airless spraying:	24-32"	200 DS or 125-DPN	10-20%
- Electrostatic spraying:	-	-	-
- Curtain coating:	-	-	-
- Fiber roller coating:	40-45"	200 DS or 125-DPN	10-15%
- Immersion:	100"	200 DS or 125-DPN	0-5%
- Brush:	-	-	-

**APPLICATION FEATURES:**

- Support: ..... All types of veneers and woods.
- Preparation of the support: ..... Eliminate the residue of sandpapering.
- Paper weight: ..... 1 - 2 coats of 140-160 gr/m<sup>2</sup> (45-90 minutes between coats).

**OBSERVATIONS:** Homogenize the varnish prior to use. It is recommended for carpentry works because of its easy application by brush, spraying and immersion. Thin the product properly in every case.

REVIEW: 2011-09-01