

Technical Data Sheet

AF60**/00 2 - PACK CLEAR WATERBORNE SELF-SEALER FOR PARQUET FLOORING

Supersedes previous issue dated 03.03.15

DATE 10/02/17

Versions:	05, 20, 30, 50 gloss
Area of use:	Specifically formulated for parquet floors.
Method of use:	Brush Roller: thin 3 - 5% with XA4026/00

Technical characteristics

Solids content (%):	31 ± 2		
Specific gravity (kg/l):	1.030 ± 0.030		
Viscosity (DIN 4 at 20°C):	18" ± 3"		
Mixing procedure:		by weight (kg)	by volume (l)
Part A	AF60**/00	100	100
Part B (hardener)	AH1547/00	10	10
Thinner	XA4026/00	3 - 5	3 - 5

General characteristics

Pot-life at 20°C:	5 - 6 hours	
Drying time (80 g/m² at 20°C 65% humidity):	Dust free	60'
	Touch dry	90'
	Overcoatable:	3 hours
	Sandable:	12 hours
	Foot traffic:	24 hours
Recommended application weight (g/m²):	Min. 60, max. 120	
Spreading rate (m²/kg):	8 - 16	
Number of coats:	Max. 3.	
Shelf-life (months):	15	

AF60**/00 is a two-pack clear non-yellowing waterborne self-sealer topcoat for use on parquet flooring, an application that requires special characteristics of elasticity, hardness, abrasion and chemical resistances, ease of application by roller and brush, and ease of touching-up and maintenance.

This two-pack product is helpful with some resinous timbers (such as iroko, merbau, etc.) who contain coloured substances that tend to be dissolved by one-pack products during application.

AF60**/00 + 10% AH1547/00 meets requirement according to ASTM D2047 "Standard Test Method for Static Coefficient of Friction of Polished-Coated Flooring Surfaces as Measured by the James Machine".

COMPANY WITH
MANAGEMENT SYSTEM
- UNI EN ISO 9001 -
- UNI EN ISO 14001 -

Sherwin-Williams Italy S.r.l. – con unico socio
Via del Fiffò, 12 - 40065 Pianoro (BO) - Italia - C.P. 18
tel. +39 051 770 511 - fax +39 051 777 437
www.sayerlack.com
Cod. Fisc. e Reg. Impr. Bo 08866930152
P. IVA: IT 00494251200 - R.E.A. n. 313180
Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531

Company under the direction and coordination of The Sherwin-Williams Company, USA

Method of use

On untreated surfaces fill any cracks using binder XT0590/00 mixed with the sawdust obtained by wood floor smoothing. To this purpose, also AU0447/00 or AF60**/00 can be used.

When the filler has dried, sand the floor carefully using 80 - 120 grit sandpaper. Remove the sanding dust with a vacuum cleaner before applying the coating.

Apply the first coat of AF60**/00 mixed with 5 - 10% of AH1547/00, making sure that the product is well spread and there are no areas of build-up.

After 12 hours at least, when drying is complete, the product is ready for sanding. It is preferable to sand manually using 150 - 180 grit paper or with mechanical systems using 220 - 240 grit paper. Then apply a second coat and, following the same method, the third coat.

Do not allow the product to build up in any areas and make sure that it is spread uniformly and with the recommended application weight of about 80 - 120 g/m² for each coat. This can easily be achieved using normal brush application. Higher application weights require much longer drying times.

For maintenance of parquet floors already coated with AF60**/00 or other types of clear coating (including solvent-based coatings), sand well using 150 grit sandpaper, clean the substrate, then apply one or two coats of AF60**/00 as described above. Make sure that the surfaces are free of grease and/or synthetic wax.

Spray application of AF60**/00 is not recommended. Actually, with this application method it is easy to exceed in quantity with the consequent possibility of several inconveniences such as detachment of the coating film from the wood substrate. In case spray application is strictly required, extreme attention must be paid to application weights or a different product must be chosen.

Special instructions

- Accidental application of thick layers of product may cause spots and cissing and slow down drying to such an extent that the film lifts from the wood.
- Keep from freezing: store in areas where temperatures do not fall below 5°C.
- During application and drying, the ambient temperature and the temperature of the coating must be no lower than 10°C. At lower temperatures drying takes longer.
- Use only drinking water for thinning.
- Mix the product using a stick or a spatula. Avoid stirring too vigorously not to incorporate air in the product which may lead to the formation of bubbles during application.
- Add AH1547/00 isocyanic crosslinker slowly while stirring the product for a few minutes. Wait another few minutes before thinning with 3 - 5% water, then stir again. The blend is now ready for application.
- Ventilate the room during and after application to improve drying.
- The coated floor is ready for foot traffic the next day, final hardness is achieved after 72 hours.
- After application wait 72 hours before placing furniture or carpets on the floor.
- For the first 2 - 3 weeks the coating is not perfectly dry and remains slightly sensitive to water. If the floor is washed and/or water deposits in some areas after treatment, this may give rise to reversible blooming on the film of coating.
- Wash working tools immediately with water. Dried coating can be removed by washing with acetone.
- Coating residues must be disposed of in accordance with current legislation. Do not pour residues down drains.
- Due to the great number of exotic timbers available on the market, it is advisable to perform a preliminary test to verify that the product does not undergo cissing, blushing or lifting caused by substances contained in the wood.

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.