

OROPAL

INDUSTRIAL & DECORATIVE PAINTS SINCE 1923



catalogue
for the professional

**Oropal,
the future
starts
today.**

OROPAL

INDUSTRIAL & DECORATIVE PAINTS SINCE 1923

4

ACRYLIC PAINTS

10

FAÇADE PAINTS

18

WATERPROOFERS FAÇADES
AND ROOFS

21

MULTI-SURFACE AND
HEAT-RESISTANT ENAMELS

27

PAINTS FOR SPORTS FACILITIES

32

PRIMERS AND SEALANTS

35

SUPPLEMENTARY PRODUCTS

37

FLOOR PAINTS

46

PAINT FOR INDUSTRY

61

FIREPROOF PAINTS

63

PIGMENT PASTES

65

SOLVENTS

66

PICTOGRAM SYMBOLS

67

CERTIFICATES

Acrylic Paints



5

WALL AND CEILING ACRYLIC PAINTS

- OROPLASTIC 40: high coverage indoor acrylic
- OROPLASTIC 45: washable indoor/outdoor acrylic

6

INDOOR/OUTDOOR ACRYLIC PAINTS

- OROPLASTIC 50: superior indoor/outdoor acrylic
- OROPLASTIC 60: premium indoor/outdoor acrylic

7

INTERIOR DECORATING ACRYLIC PAINTS

- OROPLASTIC 70: vinyl silk finish
- OROPLASTIC 80: superior vinyl finish
- OROPLASTIC 85: single-coat premium vinyl

9

SOLVENT-BASED ANTI-STAIN PAINTS

- OROCLASSIC 24: quick-drying anti-stain paint
- OROCLASSIC 25: odourless anti-stain paint



ACRYLIC



12L.

-



OROPLASTIC 40

HIGH COVERAGE INDOOR ACRYLIC

Styrene acrylic matt paint, suitable for painting ceilings, walls, and general work on all indoor masonry surfaces. Offers high coverage and whiteness. Breathable. Contains agents that give the paint anti-fungal properties.

SURFACES

Cement, concrete, plaster, stone, brick, etc.

FINISH

Matt

MAIN CHARACTERISTICS

- Indoor With anti-mould agents
- Whiteness High coverage

APPLY



DRY



30 min.

RECOAT




4-6 h.

SPREAD RATE



8-10 m²/L.

DILUTE



15% Water.
1st coat.

CLEAN WITH



Water

COLOUR CHART




White

For other colours, please check.



ACRYLIC



750ML / 4L / 15L.

6u. 2u. -



OROPLASTIC 45

WASHABLE INDOOR / OUTDOOR ACRYLIC

Washable styrene acrylic matt paint, suitable for painting ceilings, walls, work sites and general work on all indoor and outdoor masonry surfaces. Excellent whiteness and coverage. Breathable. Contains agents that give the paint anti-fungal and anti-mould properties.

SURFACES

Cement, concrete, plaster, stone, brick, etc.

FINISH

Matt

MAIN CHARACTERISTICS

- Indoor/outdoor With anti-mould agents
- Whiteness High coverage

Washable



APPLY



DRY



30 min.

RECOAT




4-6 h.

SPREAD RATE



7-9 m²/L.

DILUTE



15% Water.
1st coat.

CLEAN WITH



Water

COLOUR CHART



White

For other colours, please check.



ACRYLIC

750ML / 4L / 15L.

6u. 2u. -



OROPLASTIC 50

SUPERIOR INDOOR / OUTDOOR ACRYLIC

Styrene acrylic matt paint, suitable for indoor and outdoor decoration. With excellent whiteness and coverage, easy to apply on different materials used in construction, good spread rate, washability, with anti-fungal and anti-mould protection.

SURFACES

Cement, concrete, plaster, stone, brick, etc.

FINISH

Matt

MAIN CHARACTERISTICS



Indoor/outdoor



With anti-mould agents



Whiteness



High coverage



Washable

APPLY



DRY

30 min.

RECOAT

4-6 h.

SPREAD RATE

7-8 m²/L.

DILUTE

15% Water.
1st coat

CLEAN WITH

Water

COLOUR CHART



White



For other colours, please check.



ACRYLIC

750ML / 4L / 15L.

6u. 2u. -



OROPLASTIC 60

PREMIUM INDOOR / OUTDOOR ACRYLIC

Styrene acrylic matt paint, suitable for indoor and outdoor decoration and protection of façades. Excellent levelling, application and washability properties. Contains agents that give the paint anti-fungal and anti-mould properties. Breathable. Good adhesion on the different materials used in construction, with excellent coverage and spread.

SURFACES

Cement, concrete, plaster, stone, brick, etc.

FINISH

Matt

MAIN CHARACTERISTICS



Indoor/outdoor



With anti-mould agents



Whiteness



Washable



High resistance to weathering

APPLY



DRY

30 min.

RECOAT

4-6 h.

SPREAD RATE

7-8 m²/L.

DILUTE

15% Water.
1st coat.

CLEAN WITH

Water

COLOUR CHART



White



For other colours, please check.



VINYL



750ML / 4L. / 15L.

6u. 2u. -

OROPLASTIC 70

VINYL SILK FINISH

Vinyl-veova acrylic matt paint, suitable for indoor and outdoor decoration. Excellent application and adhesion to different materials used in construction, providing a silk finish with very good levelling, coverage, whiteness and washability. **Allows touch-ups.** With agents that give the paint anti-fungal and anti-mould properties.

SURFACES

Cement, concrete, plaster, stone, brick, etc.

FINISH

Matt

MAIN CHARACTERISTICS

- Indoor/outdoor
- With anti-mould agents
- Excellent whiteness
- Highly washable
- Coverage

APPLY



DRY

30 min.

RECOAT

4-6 h.

SPREAD RATE

7-9 m²/L.

DILUTE

15% Water.
1st coat.

CLEAN WITH

Water

COLOUR CHART



White

For other colours, please check.



VINYL



750ML / 4L. / 15L.

6u. 2u. -

OROPLASTIC 80

SUPERIOR VINYL FINISH

Vinyl-veova acrylic matt paint, suitable for indoor and outdoor decoration. Offers a fine matt finish with good coverage and whiteness. Excellent extensibility, providing high quality decorative finishes. Contains agents that give the paint anti-fungal and anti-mould properties.

SURFACES

Cement, concrete, plaster, stone, brick, etc.

FINISH

Matt

MAIN CHARACTERISTICS

- Indoor/exterior
- With anti-mould agents
- Excellent whiteness
- Highly washable
- Coverage

APPLY



DRY

30 min.

RECOAT

4-6 h.

SPREAD RATE

8-10 m²/L.

DILUTE

15% Water.
1st coat.

CLEAN WITH

Water

COLOUR CHART



White

For other colours, please check.



VINYL



750ML/ 4L. / 15L.

6u. 2u. -

OROPLASTIC 85

SINGLE-COAT PREMIUM VINYL

Vinyl-veova acrylic matt paint, suitable for indoor and outdoor decoration. Excellent adhesion to the different materials used in construction, good levelling and application, with high wet scrub resistance. Excellent spread rate and washability.

Very good single coat coverage and excellent whiteness. Contains agents that give the paint anti-fungal and anti-mould properties.

SURFACES

Cement, concrete, plaster, stone, brick, etc.

FINISH

Matt

MAIN CHARACTERISTICS

Indoor/outdoor With anti-mould agents

Excellent whiteness Coverage

Highly washable

APPLY



DRY

30 min.

RECOAT

4-6 h.

SPREAD RATE

7-8 m²/L.

DILUTE

15% Water.
1st coat.

CLEAN WITH

Water

COLOUR CHART



White



For other colours, please check.



ACRYLIC

1KG. / 5 KG. / 20KG.

6u. 2u. -



ACRYLIC

1KG. / 5 KG. / 20KG.

6u. 2u. -

OROCLASSIC 24

QUICK-DRYING ANTI-STAIN PAINT

Anti-stain matt finish. Quick drying and high capacity to cover tobacco stains, soot, grease, etc., inside new builds, cafeterias, offices, hotels, supermarkets, building refurbishments, etc. It is breathable and does not produce any stress on the film, and can even be applied at low temperatures. **Recoatable with emulsion.**

SURFACES

Cement, concrete and similar.

FINISH

Matt

MAIN CHARACTERISTICS

Indoor Quick drying

Coverage

APPLY



DRY

20/30 min.

RECOAT

2-4 h.

SPREAD RATE

5-6 m²/Kg.

DILUTE

Brush and roller ORODIS 716, up to 5%.
Airless gun ORODIS 716, up to 10%

CLEAN WITH

Orodís 716

COLOUR CHART

White

OROCLASSIC 25

ODOURLESS ANTI-STAIN PAINT

Anti-stain matt finish. The product is odourless (use ORODIS 715 solvent), which, together with its very low toxicity when applied and its ability to cover tobacco stains, soot, grease, etc., makes it the perfect product for use inside new builds, cafeterias, offices, hotels, supermarkets, building refurbishments, etc. It is breathable and does not produce any stress on the film, and can even be applied at low temperatures.

SURFACES

Cement, concrete and similar.

FINISH

Matt

MAIN CHARACTERISTICS

Indoor Odourless

High coverage

APPLY



DRY

2 h.

RECOAT

12-24 h.

SPREAD RATE

5-6 m²/Kg.

DILUTE

Brush and roller ORODIS 715, up to 5%.
Airless gun ORODIS 715, up to 10%


CLEAN WITH

Orodís 715

COLOUR CHART

White

Façade paints



11

PREPARATIONS

- OROPRIMER 103: water-based acrylic fixing primer
- OROPRIMER 106: solvent-based acrylic fixing primer
- OROPRIMER 134: silicate-based primer

12

COATINGS

- OROLITE 121: Pliolite coating for façades
- OROKRIL 135: silicate-based coating for façades
- OROKRIL 145: silicone coating for façades
- OROKRIL 150: smooth matt coating for façades
- OROKRIL 156: premium matt coating for façades
- OROKRIL 160: 100% acrylic coating for façades
- OROKRIL 161: silk matt coating for façades
- OROKRIL 162: satin coating for façades
- OROKRIL 172: elastic coating for façades



ACRYLIC

 750ML / 4L / 15L.

 6u. 2u. -

OROPRIMER 103

WATER-BASED ACRYLIC FIXING PRIMER

Water-based acrylic fixing sealant, with high penetration power in porous substrates, for indoor and outdoor use. Suitable for preparing surfaces before painting, consolidating wall substrates of all kinds or layers of well-adhered old paint, and for varnishing bricks and stone. **High water dilution 4:1.**

SURFACES

Cement, concrete, plaster, stone, brick, etc.

FINISH

Requires finish

MAIN CHARACTERISTICS

 Indoor/
outdoor

 High penetration
power

APPLY



DRY

 30 min.


RECOAT

 2 h.

SPREAD RATE

 8-10 m²/L.

DILUTE

 4 parts water to 1 part
OROPRIMER 103

CLEAN WITH

 Water

COLOUR CHART




Colourless



ACRYLIC

 750ML / 4L / 20L.

 6u. 2u. -

OROPRIMER 106

SOLVENT-BASED ACRYLIC FIXING PRIMER

Very low viscosity solvent-based acrylic fixing sealant for indoor and outdoor use. Compacts, waterproofs and increases concrete strength. It is breathable, has good resistance to the alkalinity of concrete, and protects the substrate from atmospheric variations.

SURFACES

Cement, concrete, plaster, stone, brick, etc.

FINISH

Matt

MAIN CHARACTERISTICS

 Indoor/
outdoor

 High penetration
power

APPLY




DRY

 1 h.

RECOAT

 24 h.


SPREAD RATE

 8-14 m²/L.

DILUTE

 Up to 5% of
ORODIS 719

CLEAN WITH

 Orodis 719

COLOUR CHART



Colourless



SILICATE



OROPRIMER 134

SILICATE-BASED PRIMER

Water-based potassium silicate sealing primer, suitable for indoor and outdoor use. Fixes the mineral substrates and gives them uniform absorption, preparing the surface for subsequent application of the silicate-based finish. Excellent adhesion, highly breathable, high resistance to atmospheric agents.

Resistant to microorganisms.


SURFACES

Cement, concrete and mineral surfaces except plaster.

FINISH

Matt


MAIN CHARACTERISTICS



APPLY




DRY




RECOAT



SPREAD RATE



DILUTE




CLEAN WITH



COLOUR CHART



Colourless





PLIOLITE

750ML / 4L / 20L

6u. 2u. -



SILICATE

15L

-

OROLITE 121

PLIOLITE COATING FOR FAÇADES

Solvent-based façade coating based on Pliolite resins with a matt finish, excellent resistance to weathering and alkalinity. Has very good perspiration thanks to its micropores. Excellent application and fixation on the substrate, high penetration power and impermeability. Can be applied at low temperatures. Its high coverage and capacity to conceal stains make it an ideal product for restoring dirty and poorly maintained walls.

SURFACES

Cement, concrete, plaster, stone, brick, etc.

FINISH

Matt

MAIN CHARACTERISTICS

- Indoor/outdoor
- High adhesion
- High durability
- High breathability
- Resistance to weathering

APPLY



DRY

2h.

RECOAT

12-24h.

SPREAD RATE

8-11 m²/L.

DILUTE

Up to 10% with ORODIS 719 1st coat

CLEAN WITH

Orodis 719

COLOUR CHART



White

For other colours, please check.

OROKRIL 135

SILICATE-BASED COATING FOR FAÇADES

Water-based mineral coating based on potassium silicate. Pure matt finish, high quality and breathability. Reacts with the mineral substrate, achieving excellent adhesion and a very resistant film. High alkalinity product that helps prevent mould.

SURFACES

Cement, concrete and mineral surfaces except plaster.

FINISH

Pure matt

MAIN CHARACTERISTICS

- Indoor/outdoor
- Washable
- Impermeability
- High durability
- High breathability
- Adhesion
- With anti-mould agents

APPLY



DRY

1-2h.

RECOAT

24h.

SPREAD RATE

5-7 m²/L.

DILUTE

15% Water. 1st coat.

CLEAN WITH

Water

COLOUR CHART



White

For other colours, please check.



ACRYLIC



OROKRIL 145

SILICONE COATING FOR FAÇADES

Impermeable water-based silica coating, suitable for old lime surfaces and indoor and outdoor masonry surfaces in general. Easy to apply, good spread rate, levelling, excellent silky matt finish. High durability and impermeability. With agents that give the paint anti-fungal and anti-mould properties.

SURFACES

Cement, concrete, lime, plaster, stone and brick.

FINISH

Silk matt

MAIN CHARACTERISTICS

- Indoor/outdoor
- With anti-mould agents
- Impermeability
- High durability
- Waterproof
- Washable

APPLY



DRY

30 min.

RECOAT

6-12 h.

SPREAD RATE

7-9 m²/L.

DILUTE

15% Water.
1st coat.

CLEAN WITH

Water

COLOUR CHART



White



ACRYLIC



OROKRIL 150

SMOOTH MATT COATING FOR FAÇADES

Special water-based washable matt coating for façades. Designed based on 100% acrylic polymers, suitable for indoor and outdoor use, with excellent adhesion to the different materials used in construction, good levelling, application and washability, with a polished, matt finish. Contains agents that give the paint anti-fungal and anti-mould properties.

SUPERFICIES

Cement, concrete, plaster, stone, brick, etc.

FINISH

Matt

MAIN CHARACTERISTICS

- Indoor/outdoor
- Washable
- Impermeability
- High durability
- With anti-mould agents

APPLY



DRY

30 min.

RECOAT

6-12 h.

SPREAD RATE

6-8 m²/L.

DILUTE

15% Water.
1st coat.

CLEAN WITH

Water

COLOUR CHART

- White
- Bone
- Champagne
- Sand
- Beige
- Mist
- Mocha
- Coral
- Pink
- Light grey
- Stone

For other colours, please check.

*Pre-approval required



ACRYLIC

750ML / 4L / 15L

6u. 2u. -



OROKRIL 156

PREMIUM MATT COATING FOR FAÇADES

Water-based matt coating based on styrene acrylic paint, for indoor and outdoor decoration due to its good impermeability and resistance to atmospheric agents. Breathable to water vapour and CO₂. Contains agents that give the paint anti-fungal and anti-mould properties.

SURFACES

Cement, concrete, plaster, stone, brick, etc.

FINISH

Matt

MAIN CHARACTERISTICS

- Indoor/outdoor
- With anti-mould agents
- Whiteness
- Washable

APPLY



DRY

30 min.

RECOAT

4-6 h.

SPREAD RATE

7-8 m²/L.

DILUTE

15% Water.
1st coat.

CLEAN WITH

Water

COLOUR CHART

46 COLOURS.

See OROKRIL colour chart on page 17.

For other colours, please check.

*Pre-approval required



ACRYLIC

750ML / 4L / 15L

6u. 2u. -



OROKRIL 160

100% ACRYLIC COATING FOR FAÇADES

Water-based matt coating based on 100% acrylic paint. Designed especially for façades. High impermeability, breathability, washability, good coverage and resistance to atmospheric agents. With agents that give the paint anti-fungal and anti-mould properties.

SURFACES

Cement, concrete, plaster, stone, brick, etc.

FINISH

Matt

MAIN CHARACTERISTICS

- Indoor/outdoor
- With anti-mould agents
- Impermeability
- High durability
- Washable
- Washable

APPLY



DRY

30 min.

RECOAT

4-12 h.

SPREAD RATE

7-8 m²/L.

DILUTE

15% Water.
1st coat.

CLEAN WITH

Water

COLOUR CHART

46 COLOURS.

See OROKRIL colour chart on page 17

For other colours, please check.

*Pre-approval required





ACRYLIC

750ML / 4L / 15L

6u. 2u. -



ACRYLIC

750ML / 4L / 15L

6u. 2u. -



OROKRIL 161

SILK MATT COATING FOR FAÇADES

Water-based acrylic paint silk matt coating with high washability and scrub resistance. Highly resistant to weathering, it provides excellent protection for façades, is both breathable and waterproof, and offers excellent coverage.

With agents that give the paint anti-fungal and anti-mould properties.

SURFACES

Cement, concrete, plaster, stone, brick, etc.

FINISH

Silk matt

MAIN CHARACTERISTICS

- Indoor/outdoor
- With anti-mould agents
- Impermeability
- High durability
- Breathable
- Washable

APPLY



DRY

30 min.

RECOAT

4-12 h.

SPREAD RATE

7-9 m²/L.

DILUTE

15% Water.
1st coat.

CLEAN WITH

Water

COLOUR CHART

46 COLOURS.

See OROKRIL colour chart on page 17



OROKRIL 162

SATIN COATING FOR FAÇADES

Water-based acrylic paint satin coating with high washability and scrub resistance. Excellent whiteness and coverage. Designed based on vinyl-acrylic copolymers for decorating façades. Notable for its good resistance to water, mineral salts and ultraviolet rays.

Contains agents that give the paint anti-fungal and anti-mould properties.

SURFACES

Cement, concrete, plaster, stone, brick, etc.

FINISH

Satin

MAIN CHARACTERISTICS

- Indoor/outdoor
- With anti-mould agents
- Impermeability
- High durability
- Breathable
- Washable

APPLY



DRY

30 min.

RECOAT

4-12 h.

SPREAD RATE

7-9 m²/L.

DILUTE

15% Water.
1st coat.

CLEAN WITH

Water

COLOUR CHART

46 COLOURS.

See OROKRIL colour chart on page 17

For other colours, please check.

*Pre-approval required



For other colours, please check.

*Pre-approval required





ACRYLIC



OROKRIL 172

ELASTIC COATING FOR FAÇADES

Water-based elastic matt coating based on styrene acrylic paint, especially suitable for decorating and protecting façades.

High resistance to atmospheric agents, waterproof and breathable, with excellent hardness and adhesion. Protects façades showing signs of cracks and fissures.

Anti-carbonation properties. Contains agents that give the paint anti-fungal and anti-mould properties.

SURFACES

Cement, concrete, stone and brick.

FINISH

Matt

MAIN CHARACTERISTICS

-  Indoor/outdoor
-  With anti-mould agents
-  Impermeability
-  High durability
-  Washable
-  Highly elastic

APPLY




DRY



RECOAT



SPREAD RATE



DILUTE



CLEAN WITH




COLOUR CHART

46 COLOURS.

See OROKRIL colour chart on page 17

COLOUR CHART OROKRIL



For other colours, please check.

*Pre-approval required



Waterproofers façades and roofs



19

LEAK SEALANT

OROIMPER 115: oropalgum leak sealant

OROIMPER 115 F: oropalgum fibre-reinforced leak sealant

20

WATERPROOFERS

OROIMPER 112: invisible waterproof protector for façades

OROIMPER 127: polyurethane membrane



ACRYLIC

4L / 15L.

6u. -

OROIMPER 115

OROPALGUM LEAK SEALANT

Waterproof coating based on styrene acrylic emulsion. Suitable for waterproofing roofs (terraces, rooftops, party walls), easy to apply, providing a continuous, thick coating in order to repair or prepare areas liable to crack. Withstands outdoor ageing, and maintains elasticity below 0°C. Can be bolstered with special fibres and fabrics. Non-continuously walkable or passable, with protection from soiling. Contains agents that give the paint anti-fungal and anti-mould properties.

SURFACES

Cement, concrete, stone and brick.

FINISH

Matt

MAIN CHARACTERISTICS

- Indoor/outdoor
- Passable
- Waterproof
- Highly elastic
- With anti-mould agents

APPLY



DRY

4-12 h.

RECOAT

18-24 h.

SPREAD RATE

 1,5-2,5 m²/L.

DILUTE

 15% Water.
1st coat.

CLEAN WITH

Water

COLOUR CHART



ACRYLIC

4L / 15L.

6u. -

OROIMPER 115 F

OROPALGUM FIBRE-REINFORCED LEAK SEALANT

The Oropalgum fibre-reinforced format has glass fibre for increased resistance to expansion and contraction, minimising the appearance of cracking on the treated surface.

SURFACES

Cement, concrete, plaster, stone and brick.

FINISH

Matt

MAIN CHARACTERISTICS

- Indoor/outdoor
- Passable
- Waterproof
- Highly elastic
- With anti-mould agents

APPLY



DRY

4-12 h.

RECOAT

18-24 h.

SPREAD RATE

 1,5-2,5 m²/L.

DILUTE

 15% Water.
1st coat.

CLEAN WITH

Water

COLOUR CHART





SILOXANE

750ML / 4L / 20L.

6u. 2u. -



POLYURETHANE

750ML / 4L / 20L.

6u. 2u. -

OROIMPER 112

INVISIBLE WATERPROOF PROTECTOR FOR FAÇADES

Siloxane-based, colourless, transparent and waterproof, suitable for protecting and waterproofing façades without altering the initial appearance of the substrate. Prevents water from passing through the façade, without altering its breathability. Excellent application and quick drying.

SURFACES

Cement, concrete, plaster, stone and brick.

FINISH

Without finish

MAIN CHARACTERISTICS

- Outdoor
- Waterproof
- Impermeability
- Breathable

APPLY



DRY

30 min.

RECOAT

4-6 h.

SPREAD RATE

8-10 m²/L.

DILUTE

Not required

CLEAN WITH

Orodis 719

COLOUR CHART



Colourless

OROIMPER 127

POLYURETHANE MEMBRANE

Elastic, colourless, waterproof polyurethane membrane, suitable for waterproofing terraces and façades subject to demanding conditions. Highly durable, resistant single-component satin product, suitable for **intense pedestrian traffic**. Good adhesion on common surfaces in the construction industry. **High mechanical strength**.

Contains agents that give the paint anti-fungal and anti-mould properties.

SURFACES

Cement, concrete, stone and brick, etc.

FINISH

Satin

MAIN CHARACTERISTICS

- Impermeability
- With anti-mould agents
- High elasticity

APPLY



DRY

6-12 h.

RECOAT

12-24 h.

SPREAD RATE

5-7 m²/L.

DILUTE

Diluting is not recommended

CLEAN WITH

Water


COLOUR CHART



Colourless

For other colours, please check.

Multi-surface and heat-resistant enamels



22

WATER-BASED ENAMELS:

- OROLUX 220: water-based matt enamel
- OROLUX 222: water-based satin enamel
- OROLUX 224: water-based gloss enamel

24

SOLVENT-BASED ENAMELS:

- OROLEX 260: synthetic matt enamel
- OROLAK 272: polyurethane satin lacquer
- OROLEX 284: antioxidant synthetic gloss enamel

26

SOLVENT-BASED HEAT-RESISTANT ENAMELS:

- OROMEL 502: heat-resistant enamel 300°C
- OROMER 503: heat-resistant enamel 600°C



ACRYLIC



ACRYLIC



250ML./ 750ML. / 4L.

8u. 6u. 2u.



250ML./ 750ML. / 4L.

8u. 6u. 2u.

OROLUX 220

WATER-BASED MATT ENAMEL

Water-based acrylic matt enamel. Formulated with non-yellowing resins. Particularly suitable as a finish for wood, metal or masonry substrates. Indoor and outdoor use. Formula free of aliphatic and aromatic solvents and toxic pigments. Environmentally friendly, offering a pleasant experience in homes. Single-coat finish with good levelling and washability.

SURFACES

Multi-surface

FINISH

Matt

MAIN CHARACTERISTICS

- Indoor/outdoor
- Multi-surface
- Good hardness
- High coverage

APPLY



DRY

20 min.

RECOAT

2-4 h.

SPREAD RATE

11-15 m²/L.

DILUTE

Water

CLEAN WITH

Water

COLOUR CHART

20 COLOURS.

See OROLUX colour chart on page 23

OROLUX 222

WATER-BASED SATIN ENAMEL

Water-based acrylic satin enamel. Resin-based formula for good gloss retention and no yellowing. Particularly suitable as a finish for wood, metal or masonry substrates. Indoor and outdoor use. Formula free of aliphatic and aromatic solvents and toxic pigments. Environmentally friendly, offering a pleasant experience in homes. Single-coat finish with good levelling and washability.

SURFACES

Multi-surface

FINISH

Satin

MAIN CHARACTERISTICS

- Indoor/outdoor
- Multi-surface
- Good hardness
- High coverage

APPLY



DRY

20 min.

RECOAT

2-4 h.

SPREAD RATE

10-14 m²/L.

DILUTE

Water

CLEAN WITH

Water

COLOUR CHART

20 COLOURS.

See OROLUX colour chart on page 23



ACRYLIC



250ML / 750ML / 4L

8u. 6u. 2u.

COLOUR CHART OROLUX



OROLUX 224

WATER-BASED GLOSS ENAMEL

Water-based acrylic gloss enamel. Resin-based formula for good gloss retention and no yellowing. Particularly suitable as a finish for wood, metal or masonry substrates. Indoor and outdoor use. Formula free of aliphatic and aromatic solvents and toxic pigments. Environmentally friendly, offering a pleasant experience in homes. Single-coat finish with good levelling and washability.

SURFACES

Multi-surface

FINISH

Gloss

MAIN CHARACTERISTICS



Indoor/outdoor



Multi-surface



Good hardness



High coverage

APPLY



DRY

20 min.

RECOAT

2-4 h.

SPREAD RATE

10-13 m²/L.

DILUTE

Water

CLEAN WITH

Water

COLOUR CHART

20 COLOURS.

See OROLUX colour chart on page 23

For other colours, please check.





SYNTHETIC

750ML. / 4L.

6u. 2u.



SYNTHETIC

250ML. / 750ML. / 4L. / 20L.

8u. 6u. 2u. -

OROLEX 260

SYNTHETIC MATT ENAMEL

Matt enamel with soft touch. Contains corrosion inhibitors that provide antioxidant properties. Good levelling, and excellent brushable consistency. Recommended as a finishing coat for doors, windows, baseboards, frames, cabinets, etc., both indoors and outdoors, etc.

SURFACES

All kinds of suitably prepared surfaces.

FINISH

Matt

MAIN CHARACTERISTICS

Indoor/outdoor Smooth texture

APPLY



DRY

4-6 h.

RECOAT

24 h.

SPREAD RATE

14-19 m²/L.

DILUTE

Brush and roller: Undiluted or up to 5% ORODIS 719. Spray gun: Up to 15% ORODIS 717

CLEAN WITH

Orodis 719

COLOUR CHART

White Black

For other colours, please check.

OROLAK 272

POLYURETHANE SATIN LACQUER

Satin-finish lacquer formulated with urethane synthetic resins. Contains corrosion inhibitors that provide antioxidant properties. Offers a lacquer finish with a silk touch and good coverage, with high scrub resistance. Especially recommended for lacquering furniture, doors, frames, etc. Designed to withstand temperatures up to 100°C, making it useful for decorating metal elements.

SURFACES

All kinds of suitably prepared surfaces.

FINISH

Satin

MAIN CHARACTERISTICS

Indoor/outdoor Antioxidant

Smooth texture 100°C

Good hardness

APPLY



DRY

2-3 h.

RECOAT

12 h.

SPREAD RATE

13-18 m²/L.

DILUTE

Brush and roller: Undiluted or up to 5% ORODIS 719. Spray gun: Up to 20% ORODIS 717

CLEAN WITH

Orodis 719

COLOUR CHART

White Black

For other colours, please check.



SYNTHETIC

250ML / 750ML / 4L.
8u. 6u. 2u.



OROLEX 284

SYNTHETIC ENAMEL ANTIOXIDANT GLOSS

Synthetic alkyd high-gloss enamel for indoor and outdoor protection and decoration. Contains corrosion inhibitors that provide antioxidant properties. High coverage and levelling. High resistance and stability to yellowing. Classification B-s1,d0.






SURFACES

All kinds of suitably prepared surfaces.

FINISH

Gloss

MAIN CHARACTERISTICS

-  Indoor/outdoor
-  Fireproof
-  High durability
-  Antioxidant
-  High coverage

APPLY




DRY



RECOAT



SPREAD RATE



DILUTE

Brush and roller:
Undiluted or up to 3% ORODIS 719
Spray gun:
Up to 15% with ORODIS 717
Airless: Up to 5% with ORODIS 717

CLEAN WITH



COLOUR CHART OROLEX 284



COLOUR CHART

20 COLOURS.

See OROLEX 284 colour chart



SYNTHETIC

750ML. / 4L.

6u. 2u.



SILICONE

4L. / 20L.

2u. -

OROMEL 502

HEAT-RESISTANT ENAMEL 300°C

Enamel with **luminous metallic** appearance. Formulated with special pigments not suitable for surfaces exposed to continuous friction. Good resistance to outdoor environments. Withstands temperatures of 200°C, and even up to 300°C for short intervals.

SURFACES

Iron and steel.

FINISH

Satin

MAIN CHARACTERISTICS

Resistant up to 300°C

APPLY



DRY

1 h.

RECOAT

24 h.

SPREAD RATE

14-18 m²/L.

DILUTE

Brush and roller:
Not diluted
 Gun:
up to 10% with
ORODIS 716

CLEAN WITH

ORODIS 716

COLOUR CHART



Silver

OROMEL 503

HEAT-RESISTANT ENAMEL 600°C

Paint formulated with silicone resins. These special resins react as of temperatures of 350°C, generating a rigid matrix with a crystalline structure similar to quartz. The film loses all its elasticity at higher temperatures, becoming matt and microporous with good resistance to solvents.

Not applying thicknesses greater than 20 µm is recommended in order to avoid adhesion problems

once the parts have cooled (this must be gradual and not abrupt).

SURFACES

Iron, Steel, Aluminium, Galvanized.

FINISH

Matt

MAIN CHARACTERISTICS

Withstands up to 600°C High adhesion

APPLY



DRY

20-40 min.

RECOAT

1 h.

SPREAD RATE

6-10 m²/L.

DILUTE

Up to 10%
ORODIS 716

CLEAN WITH

Up to 10%
ORODIS 716

COLOUR CHART



Silver



Black

Paints for sports facilities



28

POOLS

- OROSPORT 303: water-based paint for pools
- OROSPORT 313: chlorinated rubber-based paint for pools
- OROSPORT 315: chlorinated rubber-based semi-matt paint for pools

30

SPORTS FACILITIES

- OROSPORT 307: acrylic paint for sports tracks
- OROSPORT 320: chlorinated rubber paint for pelota courts

31

VELODROMES

- OROSPORT 325 FIXING PRIMER
 - OROSPORT 330 STRAIGHTS
 - OROSPORT 331 ENTRY EXIT CANTS
 - OROSPORT 332 CANTS
- G-0 (gradients less than 10°)
 - G-1 (gradients between 10-25°)
 - G-2 (gradients between 25-45°)



ACRYLIC

4L. / 15L.

2u. -



CHLORINATED RUBBER

5KG. / 25KG.

2u. -

OROSPORT 303

WATER-BASED PAINT FOR POOLS

Water-based acrylic matt paint, specifically designed for painting cement and concrete pools. Its characteristics include quick drying, **good repaintability** with no need for sanding, high adhesion and coverage, and outstanding resistance to ageing due to UV rays. **Protection from fungi and algae contamination.**

SURFACES

Cement and concrete.

FINISH

Matt

MAIN CHARACTERISTICS

☑ Quick drying ☀ Resistant to UV

🔪 Excellent adhesion

APPLY



DRY

🕒 30-60 min.

RECOAT

🕒 6-12 h.

SPREAD RATE

📏 7-9 m²/L.

DILUTE

💧 Up to 15% water
1st coat

CLEAN WITH

🚰 Water

FILL POOL

1 Week

COLOUR CHART



Caribbean sea blue

For other colours, please check.

OROSPORT 313

CHLORINATED RUBBER-BASED PAINT FOR POOLS

Chlorinated rubber high-coverage paint, designed especially for new pools or pools previously painted with chlorinated rubber.

It is also a quick-drying paint that is easy to repaint. Waterproof, smooth, matt finish. **Resistant to substrate alkalinity.** Excellent adhesion on cement and concrete substrates. Good chemical and weather resistance. Efficient against contamination due to fungi and algae.

SURFACES

Cement and concrete.

FINISH

Matt

MAIN CHARACTERISTICS

☑ Quick drying 🔪 Excellent adhesion

APPLY



DRY

🕒 15-30 min.

RECOAT

🕒 6-8 h.

SPREAD RATE

📏 5-6 m²/Kg.

DILUTE

📄 Up to 15% of ORODIS 719
1st coat

CLEAN WITH

📄 ORODIS 719

FILL POOL


1 Week

COLOUR CHART



Caribbean sea blue

For other colours, please check.



CHLORINATED RUBBER

 4L / 20L.

 2u. -

OROSPORT 315

CHLORINATED RUBBER-BASED DEMI-MATT PAINT FOR POOLS

Chlorinated rubber paint for pools, highly resistant to chlorinated water. The product's thermoplastic resins ensure quick drying and easy repainting. Waterproof, smooth, semi-matt finish. **Resistant to substrate alkalinity.** Excellent adhesion on cement and concrete substrates. Good chemical and weather resistance.

Reinforced protection from fungi and algae contamination.

SURFACES

Cement and concrete.

FINISH

Demi-mate


MAIN CHARACTERISTICS

 Excellent adhesion

APPLY




DRY

 30-60 min.


RECOAT

 8-12 h.

SPREAD RATE

 7-8 m²/L.

DILUTE

 Up to 15% of ORODIS 719 1st coat

CLEAN WITH

 ORODIS 719

FILL POOL

1 Week

COLOUR CHART



Caribbean sea blue

For other colours, please check.





ACRYLIC

4L / 15L

2u. -



CHLORINATED RUBBER

4L / 20L

2u. -

OROSPORT 307

ACRYLIC PAINT FOR SPORTS TRACKS

Water-based acrylic matt coating with anti-dust component for indoor and outdoor use, especially recommended for painting tennis, paddle, squash, pelota courts, etc. Scrub resistant, and excellent resistance to ageing caused by UV rays.

SURFACES

Cement, concrete and asphalt.

FINISH

Matt

MAIN CHARACTERISTICS



Indoor/outdoor



Resistant to friction



Resistant to UV

APPLY



DRY

30 min.

RECOAT

4-6 h.

SPREAD RATE

6-9 m²/L.

DILUTE

Up to 10% water
1st coat

CLEAN WITH

Water

COLOUR CHART



White



Tennis sport green



Grey



Red rust

OROSPORT 320

CHLORINATED RUBBER PAINT FOR PELOTA COURTS

Paint for cement pelota courts, formulated with chlorinated rubber resins and anti-abrasion loads, making it highly resistant to friction. Also resistant to impacts. The product's thermoplastic resins ensure quick drying and easy repainting. Waterproof. Especially recommended for painting concrete and cement squash and pelota courts. **Resistant to substrate alkalinity.** Excellent adhesion. Good chemical and weather resistance.

SURFACES

Cement and concrete

FINISH

Matt

MAIN CHARACTERISTICS



Scrub and impact resistant



Excellent adhesion

APPLY



DRY

30-60 min.

RECOAT

8-12 h.

SPREAD RATE

7-8 m²/L.

DILUTE

Up to 15% of ORODIS 719
1st coat

CLEAN WITH

ORODIS 719

COLOUR CHART



White



Medium green

OROPAL

INDUSTRIAL & DECORATIVE PAINTS SINCE 1923

Velodromes


**NON-SLIP FINISHES DESIGNED
ESPECIALLY FOR VELODROME TRACKS.**

OROSPORT 325 FIXING PRIMER
OROSPORT 330 STRAIGHTS
OROSPORT 331 TRANSITIONS
OROSPORT 332 CAMBERS

G-0 (slopes less than 10°)
G-1 (slopes between 10-25°)
G-2 (slopes between 25-45°)



Primers and sealants



33

MULTIPURPOSE

OROPRIMER 210: water-based multipurpose primer

OROPRIMER 446: solvent-based multipurpose primer

34

PRIMER AND SEALANT

OROPRIMER 415: antioxidant red rust primer

OROPRIMER 401: synthetic sealant



ACRYLIC

750ML. / 4L. / 15L.

6u. 2u. -



ACRYLIC

750ML. / 4L.

6u. 2u.

OROPRIMER 210

WATER-BASED MULTIPURPOSE PRIMER

Water-based acrylic primer. Excellent adhesion on a wide variety of suitably prepared surfaces (iron, aluminium, galvanised metal, plaster, wood, polyester, etc.). Quick drying and low odour. The product is efficient as an antioxidant for iron. No lead or chromates. Repaintable with a wide variety of paints.

SURFACES

Iron, aluminium, galvanised metal, copper, wood, plaster, pvc, polyester, glass and cement.

FINISH

Matt

MAIN CHARACTERISTICS

- Indoor / outdoor
- Antioxidant
- No yellowing
- High adhesion

APPLY



DRY

30-60 min.

RECOAT

2-4h 1k
24h. 2k

SPREAD RATE

11-14 m²/L.

DILUTE

Spray gun: Up to 5% water

CLEAN WITH

Water

COLOUR CHART



For other colours, please check.

OROPRIMER 446

SOLVENT-BASED MULTIPURPOSE PRIMER

One-component primer based on thermoplastic acrylic copolymers, with excellent fixation on different substrates that are difficult to adhere to, such as aluminium, galvanised metal, PVC, ceramic and glass. Very quick drying and easy to sand. Product designed for finish with two-component paints.

SURFACES

Plaster, concrete, glass, ceramics and metal and plastic surfaces.

FINISH

Semi-matt

MAIN CHARACTERISTICS

- High adhesion
- Ultra quick drying

APPLY



DRY

10-15 min.

RECOAT

2-4 h.

SPREAD RATE

8-11 m²/L

DILUTE

Brush up to 5% ORODIS 720
Spray gun: 30-50% of ORODIS 721

CLEAN WITH

ORODIS 721

COLOUR CHART



For other colours, please check.



SYNTHETIC

750ML. / 4L. / 20L.

6u. 2 -



SYNTHETIC

750ML. / 4L. / 20L.

6u. 2 -

OROPRIMER 415

ANTIOXIDANT RED RUST PRIMER

Quick-drying alkyd primer for iron, with pigments that give the paint high anti-corrosive power. Easy to apply, offering good humidification of the substrate.

Does not contain lead. High indoor-outdoor durability.

SURFACES

Iron and steel.

FINISH

Matt

MAIN CHARACTERISTICS

High anti-corrosive power

APPLY



DRY

1-2 h.

RECOAT

6-12 h.

SPREAD RATE

9-12 m²/L.

DILUTE

Brush up to 3% ORODIS 719.
Spray gun up to 10% ORODIS 719

CLEAN WITH

ORODIS 719

COLOUR CHART



OROPRIMER 401

SYNTHETIC SEALANT

Air-drying synthetic primer for preparing plaster and wood substrates. Its good levelling and high sealing power combine with its excellent repaintability, making it ideal as an intermediate layer for enamels.

High sandability.

SURFACES

Plaster and wood.

FINISH

Matt

MAIN CHARACTERISTICS

Levelling Adhesion

APPLY



DRY

2-4 h.

RECOAT

12-24 h.

SPREAD RATE

13-16 m²/L.

DILUTE

Brush and roller:
Up to 3% of ORODIS 719
Airmix-Airless:
Up to 5% with ORODIS 717
Spray gun:
Up to 20% with ORODIS 717

CLEAN WITH

ORODIS 719

COLOUR CHART



For other colours, please check.

Supplementary products



36

SUPPLEMENTARY PRODUCTS

OROTINT 15: water-based colourant

OROPRIMER 440: water oxide converter



125ML. / 1L.

24u. 6u.



ACRYLIC

125ML. / 250ML. / 1L.

24u. 6u. 5u.

OROTINT 15

WATER-BASED COLOURANT

Concentrated plastic colourants compatible with our emulsions, miscible with each other. Especially suitable for personalised colours in emulsions. The product is manufactured in the following colours: ochre, red rust and black (for both indoor and outdoor use) and blue, yellow, mountain green and red (for indoor use only). Does not alter the quality of the paint.

Micro-dispersed pigments.

ADDITION: 0-5%.


MAIN CHARACTERISTICS

High compatibility

CLEAN WITH

Water

COLOUR CHART



For other colours, please check.

OROPRIMER 440

WATER OXIDE CONVERTER

Oxide converter in water dispersion. Thanks to its special acid content, it converts iron oxide into a passivated surface that can be repainted with other paints (synthetic enamels, chlorinated rubber, epoxy, polyurethanes, etc.). Gives the whole system excellent anti-corrosive protection. Used in antioxidant treatments where rust cannot be completely removed and traces of oxide remain firmly attached.

SURFACES

Iron and steel.

MAIN CHARACTERISTICS



Prevents rust



Quick drying



Odourless

APPLY



DRY



30-60 min.

RECOAT



6-12 h.

SPREAD RATE



8-10 m²/L
(according to surface roughness)

DILUTE

Not diluted

CLEAN WITH



Water

COLOUR CHART



Colourless (changes to bluish black when reacting with rust)

Floor paints



38

FLOOR TREATMENT PAINT SYSTEMS

- ONE-COMPONENT PAINT SYSTEM
- TWO-COMPONENT PAINT SYSTEM

40

ONE-COMPONENT FINISHES

- OROLUR 344: road marking paint
- OROLUR 351: chlorinated rubber floor paint

41

TWO-COMPONENT PRIMERS

- OROPRIMER 361: polyurethane floor primer
- OROPRIMER 388: epoxy floor primer

42

TWO-COMPONENT FINISHES

- OROLUR 362: polyurethane satin
- OROLUR 364: polyurethane gloss
- OROLUR 380: water-based epoxy gloss
- OROLUR 384: epoxy gloss

44


SELF-LEVELLING SYSTEM

- OROPRIMER 393: 100% solids epoxy primer
- OROLUR 394: self-levelling epoxy finish 1-3 mm
- OROLUR 395: self-levelling epoxy finish 0.5 mm
- OROLUR 396: self-levelling epoxy silica

Floor treatment paint systems

Preparing the substrate

The following floor paint systems must always be applied after preparing the substrate thoroughly. As indicated in the product data sheets, the substrate must be porous, well set, dry, clean, compact and free of cracks. The image below schematically shows the composition of our systems for floors. These consist of a primer, indicated in yellow, and one or two finishing coats, in grey and green. The systems also show the usual consumption of each product in order to obtain the minimum recommended thicknesses.



ONE-COMPONENT PAINT SYSTEMS

One-component floor paints are easy to apply, and have good hardness and wear resistance properties for each of the indicated uses. These paint systems are suitable for indoor and outdoor use.

SPORTS COURTS AND CYCLE TRACKS WATER-BASED MATT ACRYLIC PAINT

1 - OROPRIMER 103	100 g/m ²
2 - OROSPORT 307	200 g/m ²
3 - OROSPORT 307	200 g/m ²



MARKINGS FOR ROADS AND INDUSTRIAL UNITS QUICK DRYING MATT ACRYLIC PAINT

1 - OROLUR 344 DILUE	100 g/m ²
2 - OROSPORT 344	220 g/m ²



WORKSHOPS, OFFICES, WAREHOUSES, PRIVATE GARAGES SOLVENT-BASED CHLORINATED RUBBER SEMI-MATT PAINT


1 - OROLUR 351-TR	100 g/m ²
2 - OROLUR 351	200 g/m ²
3 - OROLUR 351	200 g/m ²





TWO-COMPONENT PAINT SYSTEMS

Two-component systems offer superior mechanical and chemical performance to one-component systems. Application is limited by how long the mixture lasts. In the case of epoxy paints, there is also a minimum reaction temperature. The durability of the products is directly related to the thickness applied. Polyurethane paints are highly recommended for outdoor use, and can be applied at low temperatures and in high relative humidity.



CAR PARKS, INDUSTRIAL FLOORS MEDIUM TRAFFIC, LIGHT VEHICLES. THICKNESSES <500 DRY MICRONS

SOLVENT-BASED POLYURETHANE SYSTEM INDOOR-OUTDOOR gloss	1 - OROPRIMER 361	90 g/m ²
	2 - OROLUR 364	150 g/m ²
	3 - OROLUR 364	150 g/m ²
SOLVENT-BASED EPOXY SYSTEM - INDOOR gloss	1 - OROPRIMER 388	75 g/m ²
	2 - OROLUR 384	125 g/m ²
	3 - OROLUR 384	125 g/m ²
WATER-BASED EPOXY SYSTEM - INDOOR semi-gloss	1 - OROLUR 380-TR	85 g/m ²
	2 - OROLUR 380	175 g/m ²
	3 - OROLUR 380	170 g/m ²



PARKINGS, SOLS INDUSTRIELS HIGH TRAFFIC, HEAVY VEHICLES. THICKNESSES ≥500 DRY MICRONS

HIGH SOLIDS SYSTEM 0.5 mm INDOOR	1 - OROPRIMER 388	75 g/m ²
	2 - OROLUR 395	900 g/m ²
SELF-LEVELLING SYSTEM 2 mm INDOOR	1 - OROPRIMER 393	160 g/m ²
	2 - OROLUR 394	3634 g/m ²





ACRYLIC

4L. / 20L.

2u. -



CHLORINATED RUBBER

4L. / 20L.

2u. -

OROLUR 344

ROAD MARKING PAINT

Quick-drying acrylic paint for road markings. High resistance to wear and tear and weathering. Especially recommended for painting markings on streets, car parks and industrial floors, and for cement, concrete or asphalt surfaces in general. Convertible to reflective through the use of powdered or sprayed glass microspheres.

SURFACES

Cement, concrete and hard asphalt.

FINISH

Matt

MAIN CHARACTERISTICS

Quick drying High resistance to deterioration

High resistance to weathering

APPLY



DRY

15-30 min.

RECOAT

2-3 h.

SPREAD RATE

7-10 m²/L.

DILUTE

Up to 10% of ORODIS 717 1st coat.

CLEAN WITH

ORODIS 717

COLOUR CHART



White Yellow Red Blue

For other colours, please check.

OROLUR 351

CHLORINATED RUBBER FLOOR PAINT

Impermeable floor paint with anti-abrasion loads, making it highly wear resistant. The product's thermoplastic resins ensure quick drying and easy repainting. The product is resistant to acids, petrols, mineral oils and aggressive atmospheres. It offers a semi-matt finish, **efficient in protecting cement from dust.**

SURFACES

Cement and concrete.

FINISH

Semi-matt

MAIN CHARACTERISTICS

Wear resistance High chemical resistance

APPLY



DRY

30-60 min.

RECOAT

8-12 h.

SPREAD RATE

7-9 m²/L.


DILUTE

Up to 15% of ORODIS 719 1st coat

CLEAN WITH

ORODIS 719

COLOUR CHART



Colourless Medium green Pearl grey Red rust

For other colours, please check.



POLYURETHANE

4L. / 20L.

2u. -



ÉPOXY

4L. / 20L.

2u. -

OROPRIMER 361

POLYURETHANE FLOOR PRIMER

Two-component aliphatic polyurethane gloss sealant with high resistance to the outdoor environment (high protection from UV rays). Forms a hard, waterproof film that is resistant to oils, salts and petrols. Formulated especially as a fixing primer when painting concrete and cement floors. Can be left as a finish outdoors. Ideal for preparing the substrate before finishing with OROLUR 364.

SURFACES

Concrete and cement.

FINISH

Gloss

MAIN CHARACTERISTICS

- High UV resistance
- High chemical resistance
- Waterproof
- Good hardness

APPLY



DRY

1-2 h.

RECOAT

12-24 h.

SPREAD RATE

9-11 m²/L.

DILUTE

Up to 10% ORODIS 720

CLEAN WITH

ORODIS 720

MIX (4:1 by vol.)

Base

4L. 20L.

Catalyst OROCAT 714

1L. 5L.

COLOUR CHART



Colourless

OROPRIMER 388

EPOXY FLOOR PRIMER

Two-component polyamide epoxy sealant varnish with high resistance to chemicals, fats and oils. Good hardness and abrasion resistance. Highly suitable for concrete floors due to its excellent adhesion, penetration and fixation in these materials. Ideal for preparing the substrate before finishing with OROLUR 384 or OROLUR 364. Also suitable for varnishing steel.

SURFACES

Concrete, cement and steel.

FINISH

Gloss

MAIN CHARACTERISTICS

- High chemical resistance
- High penetration
- High durability
- Good adherence
- Waterproof

APPLY



DRY

4 h.

RECOAT

18-24 h.

SPREAD RATE

10-13 m²/L.

DILUTE

Up to 10% ORODIS 718

CLEAN WITH

ORODIS 718

MIX (2:1 by vol.)

Base

4L. 20L.

Catalyst OROCAT 744

2L. 10L.

COLOUR CHART



Colourless



POLYURETHANE

4L. / 20L.

2u. -

OROLUR 362

POLYURETHANE SATIN

Two-component aliphatic polyurethane satin paint with high resistance to the outdoor environment (high protection from UV rays). Forms a hard, waterproof film that is resistant to oils, salts and petrols. Formulated especially for painting concrete and cement floors.

SURFACES

Cement and concrete.

FINISH

Satin

MAIN CHARACTERISTICS



High protection from UV rays



Good hardness



Waterproof



High chemical resistance

APPLY



DRY

1-2 h.

RECOAT

After 12 h.
Up to 4 days

SPREAD RATE

9-11 m²/L.

DILUTE

Up to 15%
of ORODIS 720


CLEAN WITH

ORODIS 720

MIX (4:1 by vol.)

Base

Catalyst OROCAT 714



COLOUR CHART



Grey

For other colours, please check.



POLYURETHANE

4L. / 20L.

2u. -

OROLUR 364

POLYURETHANE GLOSS

Two-component aliphatic polyurethane paint with gloss finish for concrete and cement floors. High resistance to the outdoor environment (high protection from UV rays). Forms a hard, waterproof film that is resistant to oils, salts and petrols. Ideal as a finish for epoxy-polyurethane systems.

SURFACES

Cement and concrete.

FINISH

Gloss

MAIN CHARACTERISTICS



High protection from UV rays



Good hardness



Waterproof



High chemical resistance

APPLY



DRY

1-2 h.

RECOAT

After 12 h.
Up to 4 days

SPREAD RATE

9-11 m²/L.

DILUTE

Up to 15%
of ORODIS 720


CLEAN WITH

ORODIS 720

MIX (4:1 by vol.)

Base

Catalyst OROCAT 714



COLOUR CHART



Grey

For other colours, please check.



ÉPOXY

4KG. / 20KG.

2u.

OROLUR 380

WATER-BASED EPOXY GLOSS

Two-component water-based epoxy paint for concrete and cement floors. **Excellent mechanical and chemical properties.** Formulated with polymeric emulsions for relatively quick drying and good curing reaction for temperatures up to 10°C. Recommended for indoor use. Allows thicknesses over 100 microns to be applied. Solvent-free, it is recommended for use in schools, health centres, food industries, etc.

SURFACES

Cement and concrete.

FINISH

Gloss

MAIN CHARACTERISTICS

Good levelling Odourless indoors

APPLY



DRY

Touch dry: 2-3 h.
Hard dry: 7 days

RECOAT

After 8 h.
Up to 48 hours.

SPREAD RATE

6-8 m²/Kg.

DILUTE

Up to 10% water
1st coat

CLEAN WITH

Water

MIX (4:1 by weight)

Base

4Kg. 20Kg.

Catalyst OROCAT 734

1Kg. 5Kg.

COLOUR CHART



Grey



ÉPOXY

4L. / 20L.

2u.

OROLUR 384

EPOXY GLOSS

Two-component, polyamide epoxy resin-based enamel with high resistance to chemicals, fats and oils, excellent hardness and resistance to abrasion. Designed especially for painting industrial floors, car parks and even metal structures. Indoor product.

SURFACES

Cement and concrete.

FINISH

Gloss

MAIN CHARACTERISTICS

Good hardness Wear resistance
 Chemical resistance

APPLY



DRY

Touch dry: 4 h.
Hard dry: 7 days

RECOAT

After 24 h.
Up to 48 hours.

SPREAD RATE

12-15 m²/L.

DILUTE

Up to 20% of
ORODIS 718
1st coat

CLEAN WITH

ORODIS 718

MIX (2:1 by vol.)

Base

4L. 20L.

Catalyst OROCAT 744

2L. 10L.

COLOUR CHART



Grey



ÉPOXY

4KG. / 20KG.

2u. -



ÉPOXY

20KG.

-

OROPRIMER 393

100% SOLIDS EPOXY PRIMER

Solvent-free epoxy primer. Two-component system. High penetration and adhesion for cement and concrete. Increases compactness and mechanical strength of concrete. High levelling power and resistance to chemicals. Designed as a self-levelling primer for cement pavements before applying self-levellers, or as a protective primer.

SURFACES

Cement and concrete.

FINISH

Gloss

MAIN CHARACTERISTICS

- Solvent-free
- Good hardness
- Good self-levelling power

APPLY



DRY

Touch dry: 4 h.
Hard dry: 7 days

RECOAT

After 12 h
Up to 4 days

SPREAD RATE

5-7m²/Kg.

DILUTE

Not diluted

CLEAN WITH

ORODIS 718

MIX (2:1 by weight)

Base

Catalyst OROCAT 794

4Kg. 20Kg.

2Kg. 10Kg.

COLOUR CHART



Colourless

OROLUR 394

SELF-LEVELLING EPOXY FINISH (1-3 MM)

High thickness coating based on epoxy resins. Three-component compound (base, catalyst and silica). Product with high levelling power. Leaves a surface with **high abrasion resistance**. These properties make it particularly suitable for use in high-performance indoor flooring.

SURFACES

Cement and concrete.

FINISH

Ceramic gloss

MAIN CHARACTERISTICS

- High chemical resistance
- Good self-levelling power

APPLY



DRY

4 h. (touch)
15 h. (light traffic)
48 h. (heavy traffic)

RECOAT

15-18 h
(max. 48 h)

SPREAD RATE

0.6 m²/kg. (thickness 1 mm)
0.3 m²/kg. (thickness 2 mm)
0.2 m²/kg. (thickness 3 mm)

DILUTE

Not diluted

CLEAN WITH

ORODIS 718

MIX (4:1:5 by weight)

Base

Catalyst OROCAT 794

OROLUR 396 (silica)

20Kg.

5Kg.

25Kg.

COLOUR CHART

Grey RAL
7047

For other colours, please check.



ÉPOXY

20KG.

-



MINERAL

25KG.

-

OROLUR 395

SELF-LEVELLING EPOXY FINISH (0,5 MM)

100% solids high-thickness coating based on epoxy resins. A product with high levelling power, offering a finish with **high resistance to abrasion** and to chemical products. These properties make it particularly suitable for use in high-performance indoor flooring.

SURFACES

Cement and concrete.

FINISH

Gloss

MAIN CHARACTERISTICS

Solvent-free Good self-levelling power

High chemical resistance

APPLY



DRY



4 h. (touch)
15 h. (light traffic)
48 h. (heavy traffic)

RECOAT



15-24 h
(max. 48 h)

SPREAD RATE



1.4 m²/kg.
(thickness 0.5 mm)

DILUTE

Not diluted

CLEAN WITH



ORODIS 718

MIX (4:1 by weight)

Base

Catalyst OROCAT 794

20Kg.

5Kg.

COLOUR CHART



Grey RAL
7040

OROLUR 396

SELF-LEVELLING EPOXY SILICA

Dry quartz with particle size between 100 and 800 microns, for use as filler for self-levelling epoxy systems with thicknesses above 1 mm.



Paints for industry



47

ONE-COMPONENT PRIMERS

- OROPRIMER 406: quick-drying fireproof primer
- OROPRIMER 410: antioxidant synthetic semi-matt primer
- OROPRIMER 416: water-based antioxidant primer
- OROPRIMER 420: zinc-rich phosphate primer
- OROPRIMER 425: antioxidant primer/finish
- OROPRIMER 426: antioxidant satin primer/finish
- OROPRIMER 443: anti-corrosive phosphating shop primer
- OROPRIMER 449: zinc-rich primer

51

TWO-COMPONENT PRIMERS

- OROPRIMER 455: anti-corrosive phosphating wash primer
- OROPRIMER 485: zinc-rich phosphate epoxy primer
- OROPRIMER 494: zinc-rich epoxy primer
- OROPRIMER 495: zinc-rich epoxy primer

53

ONE-COMPONENT FINISHES

- OROMEL 501: hammertone enamel
- OROMEL 505: antioxidant metallic enamel
- OROMEL 510: antioxidant wrought iron enamel
- OROMEL 515: chlorinated rubber enamel
- OROMEL 520: quick-dry matt enamel
- OROMEL 522: quick-dry satin enamel
- OROMEL 524: quick-dry gloss enamel

57

TWO-COMPONENT FINISHES

- OROMEL 607: polyurethane textured enamel
- OROMEL 610: polyurethane matt enamel
- OROMEL 612: polyurethane satin enamel
- OROMEL 614: polyurethane gloss enamel
- OROMEL 634: water-based epoxy gloss enamel
- OROMEL 644: solvent-based epoxy enamel
- OROMEL 649: food-safe epoxy enamel



SYNTHETIC

5KG. / 25KG.
 2u. -



OROPRIMER 406

QUICK-DRYING FIREPROOF PRIMER

Quick-drying synthetic primer. Its fire reaction means it is classified as B-s1,d0. It is also antioxidant. These characteristics make it ideal as a protective undercoat for iron and steel surfaces. It is chromate- and lead-free.

SURFACES

Iron and steel.

FINISH

Matt

MAIN CHARACTERISTICS

Fireproof Quick drying

APPLY



DRY

30 min.

RECOAT

6 h.

SPREAD RATE

5-8 m²/kg.

DILUTE

Brush and roller: Up to 3% of ORODIS 719
Spray gun: Up to 10% of ORODIS 716 or ORODIS 717

CLEAN WITH

ORODIS 719

COLOUR CHART



Red rust



Grey



Yellow RAL 1003



White RAL 9003

For other colours, please check.



SYNTHETIC

5KG. / 25KG.
 2u. -

OROPRIMER 410

ANTIOXIDANT SYNTHETIC SEMI-MATT PRIMER

Air-drying synthetic primer. Its quick drying properties ensure the fast workability of parts, meaning it is used as an undercoat in construction, industrial machinery, and all types of iron and steel surfaces. Thanks to the appearance of the dry film, it can be used as a unique priming and finishing system. Provides the treated substrates with a good barrier against the effects of oxidation.

SURFACES

Iron and steel.

FINISH

Semi-matt

MAIN CHARACTERISTICS

Antioxidant Quick drying

Primer and finish system

APPLY



DRY

30-40 min.

RECOAT

24 h.

SPREAD RATE

6-10 m²/Kg.

DILUTE

Brush and roller: Up to 3% of ORODIS 719.
Spray gun: Up to 10% of ORODIS 717

CLEAN WITH

ORODIS 717

COLOUR CHART



Red rust



Grey



Yellow RAL 1003




White RAL 9003

For other colours, please check.



SYNTHETIC

 5KG. / 25KG.

 2u. -

OROPRIMER 416

WATER-BASED ANTIOXIDANT PRIMER

One-component alkyd water-based primer. The formula contains antioxidant compounds that give it high anti-corrosive power. Recommended for protecting structures and all types of iron and steel parts.

SURFACES

Iron and steel.

FINISH

Matt

MAIN CHARACTERISTICS

 Antioxidant

APPLY




DRY

 30-40 min.


RECOAT

 6-8 h.

SPREAD RATE

 7-10 m²/Kg.

DILUTE

 Spray gun: Up to 10%
Brush and roller:
Undiluted or max. 3%
water

CLEAN WITH

 Water

COLOUR CHART



Red rust



Grey



Yellow RAL
1003




White RAL
9003

For other colours, please check.



SYNTHETIC

 5KG. / 25KG.

 2u. -

OROPRIMER 420

ZINC-RICH PHOSPHATE PRIMER

Alkyd primer. The presence of zinc phosphates in its formulation gives the paint excellent anti-corrosive power. Its use is recommended for machinery, bodywork, cranes, tanks, and all types of iron and steel parts. Chromate- and lead-free.

SURFACES

Iron and steel.

FINISH

Matt

MAIN CHARACTERISTICS

 Antioxidant  Quick drying

APPLY




DRY

 1h.


RECOAT

 4-6 h.

SPREAD RATE

 8-12 m²/Kg.

DILUTE

 Brush and roller: Up to
3% of ORODIS 719
Spray gun: Up to 10%
of ORODIS 717

CLEAN WITH

 ORODIS 719

COLOUR CHART



Red rust



Grey



Yellow RAL
1003



White RAL
9003

For other colours, please check.



SYNTHETIC

5KG. / 25KG.

2u. -

OROPRIMER 425

ANTIOXIDANT PRIMER/FINISH

Alkyd semi-matt paint with antioxidant pigments that make the paint highly resistant to corrosion. This property makes the coating an ideal primer for all types of steel parts. Withstands temperatures of 150°C and peaks of 200°C.

SURFACES

Steel.

FINISH

Semi-matt

MAIN CHARACTERISTICS

- Quick drying
- Resistant up to 200°C
- Primer and finish system
- Antioxidant

APPLY



DRY

20-25 min.

RECOAT

3-4 h.

SPREAD RATE

6-9 m²/Kg.


DILUTE

Brush and roller:
Up to 3% of ORODIS 719
Spray gun up to 15% of ORODIS 716

CLEAN WITH

ORODIS 716

COLOUR CHART



For other colours, please check.



SYNTHETIC

5KG. / 25KG.

2u. -

OROPRIMER 426

ANTIOXIDANT SATIN PRIMER/FINISH

Alkyd satin paint with antioxidant pigments that make it highly resistant to corrosion. This property makes it an ideal primer for all types of steel parts. Withstands temperatures of 150°C and peaks of 200°C.

SURFACES

Steel.

FINISH

Satin

MAIN CHARACTERISTICS

- Quick drying
- Resistant up to 200°C
- Primer and finish system
- Antioxidant

APPLY



DRY

25-35 min.

RECOAT

4-6 h.

SPREAD RATE

8-10 m²/Kg.

DILUTE

Up to 15% of ORODIS 716

CLEAN WITH

ORODIS 716

COLOUR CHART



For other colours, please check.



VINYL

4L.

2u.

OROPRIMER 443

ANTI-CORROSIVE PHOSPHATING SHOP PRIMER

Vinyl one-component anti-corrosive phosphating primer. Formulated to provide good adhesion on iron, aluminium and galvanised structures. Very quick drying. **Suitable for welding.** Do not mix with other products.

SURFACES

Metal surfaces, especially aluminium and galvanised metal.

FINISH

Matt

MAIN CHARACTERISTICS

Very quick drying

Antioxidant

APPLY



DRY

10-20 min.

RECOAT

4-6 h.

SPREAD RATE

5-10 m²/L.

DILUTE

Brush: Not diluted.
Spray gun: Up to 10% of ORODIS 716

CLEAN WITH

ORODIS 716

COLOUR CHART



CHLORINATED RUBBER

750ML. / 4L.

6u. 2u.

OROPRIMER 449

ZINC-RICH PRIMER

Primer based on chlorinated rubber resins. The high zinc content in the formula ensures good protection from corrosion. Acts like galvanised metal. **Suitable for welding.** Chromate- and lead-free.

SURFACES

Iron and steel.

FINISH

Matt

MAIN CHARACTERISTICS

Antioxidant

APPLY



DRY

30-60 min.

RECOAT

6 h.

SPREAD RATE

9-11 m²/L.

DILUTE

Brush: Not diluted.
Spray gun: Up to 10% of ORODIS 719

CLEAN WITH

ORODIS 719

COLOUR CHART



Grey



VINYL



4L.



2u..

OROPRIMER 455

ANTI-CORROSIVE PHOSPHATING WASH PRIMER

Vinyl two-component phosphating primer. Thanks to its quick drying, anti-corrosive power and good adhesion, it is suitable for metal surfaces that are difficult to adhere to.

SURFACES

Aluminium, galvanised metal and alloys.

FINISH

Matt

MAIN CHARACTERISTICS

Quick drying Antioxidant

Good adhesion

APPLY



DRY

5-15 min.

RECOAT

30 min.

SPREAD RATE

10-15 m²/L.

DILUTE

Brush: Not diluted up to 15% of ORODIS 5726
Spray gun: Up to 30% of ORODIS 726

CLEAN WITH

ORODIS 726

MIX (1:1 by vol.)

Base

Catalyst OROCAT 755



4L.



4L.

COLOUR CHART



Yellowish



ÉPOXY



4L. / 20L.



2u. -

OROPRIMER 485

ZINC-RICH PHOSPHATE EPOXY PRIMER

Two-component epoxy primer.

The antioxidant pigments (Zn phosphate) give it good resistance from corrosion. Ideal as a primer before applying polyurethane-based paint on all types of metal structures. **Resistant to aggressive environments.** Validated by CIDETEC for C3-C5 systems.

SURFACES

All metal types.

FINISH

Semi-mate

MAIN CHARACTERISTICS

Antioxidant

APPLY



DRY

1-2 h.

RECOAT

12-48 h.

SPREAD RATE

8-9 m²/L.

DILUTE

Up to 15% of ORODIS 718

CLEAN WITH

ORODIS 718

MIX (4:1 by vol.)

Base

Catalyst OROCAT 744

4L. 20L.

1L. 5L.

COLOUR CHART



Red rust



Grey




Yellow RAL 1003



White RAL 9003




ÉPOXY

 4L. / 20L.

 2u. -



ÉPOXY

 4L. / 20L.

 2u. -

OROPRIMER 494

ZINC-RICH EPOXY PRIMER

Two-component epoxy primer. The primer's high zinc content ensures high resistance to corrosion. Ideal as a primer **for epoxy and polyurethane finishes** on all types of metal structures. Its qualities make it easy to apply even in **chemically aggressive environments**.

SURFACES

All metal types.

FINISH

Semi-mate

MAIN CHARACTERISTICS

 Excellent anti-corrosive power

 Easy to apply

APPLY




DRY

 30-60 min.

RECOAT

 12-48 h.

SPREAD RATE

 8-9 m²/L.

DILUTE

 Up to 15% of ORODIS 718


CLEAN WITH


 ORODIS 718

MIX (4:1 by vol.)

Base

Catalyst OROCAT 744

 4L. 20L.

 1L. 5L.

COLOUR CHART



Grey

OROPRIMER 495

ZINC-RICH EPOXY PRIMER

Extraordinary quality two-component polyamide epoxy resin-based primer. Excellent anti-corrosive power thanks to its high zinc content. Allows maximum corrosion resistance with low thicknesses. Acts like galvanised metal. Suitable for welding. Chromate- and lead-free. Validated by CIDETEC for C4-C5 systems.

SURFACES

All metal types.

FINISH

Matt

MAIN CHARACTERISTICS


 Quick drying

 Excellent anti-corrosive power

APPLY




FORCED DRYING

 10-15 min. at ambient temperature and then 30-60 min. at 70-80°C

RECOAT

 12-24 h.


SPREAD RATE

 8-10 m²/L.

DILUTE

 Up to 15% of ORODIS 718


CLEAN WITH


 ORODIS 718

MIX (4:1 by vol.)

Base

Catalyst OROCAT 744

 4L. 20L.

 1L. 5L.

COLOUR CHART



Grey



SYNTHETIC

750ML. / 4L.

6u. 2u.

OROMEL 501 HAMMERTONE ENAMEL

One-component, metallic, antioxidant enamel based on quick-drying alkyd resins, **producing a hammered effect** once applied. Decorative coating for all kinds of appliances and machinery.

SURFACES
Steel.

FINISH
Hammertone semi-gloss

MAIN CHARACTERISTICS

Antioxidant

APPLY



DRY

40-60 min.

RECOAT

12-24 h.

SPREAD RATE

9-13 m²/L.

DILUTE

Roller brush:
Not diluted.
Airliss and Airmix:
Up to 10% of
ORODIS 717

CLEAN WITH

ORODIS 717

COLOUR CHART



For other colours, please check.



SYNTHETIC

750ML. / 4L.

6u. 2u.

OROMEL 505 ANTIOXIDANT METALLIC ENAMEL

Metallic enamel with high gloss, good resistance to the outdoor environment and excellent decorative effect, applicable both outdoors and indoors on all types of suitably primed surfaces (doors, windows, furniture, street lights, fences, etc.). **Contains special pigments.**

SURFACES
Steel.

FINISH
Metallic

MAIN CHARACTERISTICS



Resistance to outdoor environments



Antioxidant



Easy to apply

APPLY



DRY

4-8 h.

RECOAT

12-24 h.

SPREAD RATE

14-21 m²/L.


DILUTE

Brush and roller: Up to 2% of ORODIS 717.
Airliss and airmix: Up to 5% of ORODIS 717

CLEAN WITH

ORODIS 719

COLOUR CHART



For other colours, please check.



SYNTHETIC

750ML. / 4L.

6u. 2u.



CHLORINATED RUBBER

750ML. / 4L. / 20L.

6u. 2u. -

OROMEL 510

ANTIOXIDANT WROUGHT IRON ENAMEL

Paint with **special pigments** and antioxidant power. Has a rough finish like wrought iron. High protection for iron and steel. Its high resistance means it can be used both indoors and outdoors.

SURFACES

Iron and steel.

FINISH

Matt wrought iron

MAIN CHARACTERISTICS

Indoor/outdoor Antioxidant

High resistance to weathering

APPLY



DRY

12-24 h.

RECOAT

3-4 h.

SPREAD RATE

9-11 m²/L.

DILUTE

Brush and roller: Up to 3% of ORODIS 719
Airless and airmix: Up to 10% of ORODIS 719

CLEAN WITH

ORODIS 719

COLOUR CHART



Grey Black

OROMEL 515

CHLORINATED RUBBER ENAMEL

Chlorinated rubber-based protective paint. The product's thermoplastic resins ensure quick drying and **easier repainting**. Offers a waterproof finish that is resistant to corrosion, acid, alkali and mineral oil. The product is designed to protect industrial iron and cement surfaces.

SURFACES

Cement and Iron.

FINISH

Semi-mate

MAIN CHARACTERISTICS

Indoor/outdoor

Antioxidant

Waterproof

Quick drying

APPLY



DRY

30-60 min.

RECOAT

8-12 h.

SPREAD RATE

7-9 m²/L.

DILUTE

Brush and roller: Up to 5% of ORODIS 719
Spray gun: Up to 15% of ORODIS 719

CLEAN WITH

ORODIS 719

COLOUR CHART



Green Grey Black



SYNTHETIC

4L. / 20L.

2u. -



SYNTHETIC

4L. / 20L.

2u. -

OROMEL 520

QUICK-DRY MATT ENAMEL

Quick-dry synthetic alkyd matt enamel for indoor and outdoor protection. Particularly suitable for painting heavy vehicles, industrial and agricultural machinery (tractors, cabins, etc.), and metal surfaces in general. Oil resistant.

SURFACES

Suitably primed metal.

FINISH

Matt

MAIN CHARACTERISTICS

- Indoor/outdoor
- High durability
- Quick drying
- Good hardness

APPLY



DRY

30-60 min.

RECOAT

6-10 h.

SPREAD RATE

8-12 m²/L.

DILUTE

Brush and roller: Up to 3% ORODIS 719
Airless and airmix: Up to 5% with ORODIS 716 or ORODIS 717
Spray gun: 15-25% with ORODIS 716 or ORODIS 717

CLEAN WITH

ORODIS 719

COLOUR CHART



White

For other colours, please check.



OROMEL 522

QUICK-DRY SATIN ENAMEL

Quick-dry synthetic alkyd satin enamel for indoor and outdoor protection. Particularly suitable for painting heavy vehicles, industrial and agricultural machinery (tractors, cabins, etc.), and metal surfaces in general. Oil resistant.

SURFACES

Suitably primed metal.

FINISH

Satin

MAIN CHARACTERISTICS

- Indoor/outdoor
- Quick drying
- Good hardness
- High durability

APPLY



DRY

30-40 min.

RECOAT

6-10 h.

SPREAD RATE

8-10 m²/L.

DILUTE

Brush and roller: Up to 3% ORODIS 719.
Airless and airmix: Up to 5% with ORODIS 716 or ORODIS 717
Spray gun: 15-25% with ORODIS 716 or ORODIS 717

CLEAN WITH

ORODIS 719

COLOUR CHART



White

For other colours, please check.





SYNTHETIC

4L / 20L

2u. -

OROMEL 524

QUICK-DRY GLOSS ENAMEL

Quick-dry synthetic alkyd synthetic enamel for indoor and outdoor protection. Particularly suitable for painting heavy vehicles, industrial and agricultural machinery (tractors, cabins, etc.), and metal surfaces in general. Oil resistant.

SURFACES

Suitably primed metal.

FINISH

Gloss

MAIN CHARACTERISTICS

-  Indoor/outdoor
-  Quick drying
-  Good hardness
-  High durability

APPLY



DRY

 30-40 min.


RECOAT

 8-12 h.

SPREAD RATE

 12-17 m²/L.

DILUTE

 Brush and roller: Up to 3% ORODIS 719.
 Airless and airmix: Up to 5% with ORODIS 716 or ORODIS 717
 Spray gun: 15-25% with ORODIS 716 or ORODIS 717

CLEAN WITH

 ORODIS 719

COLOUR CHART

 White



For other colours, please check.



POLYURETHANE

4L. / 20L.

2u. -



POLYURETHANE

4L. / 20L.

2u. -

OROMEL 607

POLYURETHANE TEXTURED ENAMEL

Two-component aliphatic polyurethane **textured enamel** with satin effect and high resistance to the outdoor environment (high protection from UV rays). Forms a hard, waterproof film that is resistant to oils. Especially suitable as a finish for industrial machinery, furniture, and all types of suitably primed metal elements requiring a uniform rough finish. Apply with spray gun.

SURFACES

Suitably prepared metal or plastic.

FINISH

Satin

MAIN CHARACTERISTICS

- Indoor/outdoor
- Good hardness
- No yellowing

APPLY



DRY

1-2 h.

RECOAT

12-24 h.

SPREAD RATE

9-11 m²/L.

DILUTE

Up to 20% ORODIS 720

CLEAN WITH

ORODIS 720

MIX (5:1 by vol.)

Base

4L. 20L.

Catalyst OROCAT 714

0,8L. 4L.

COLOUR CHART



White

For other colours, please check.

OROMEL 610

POLYURETHANE MATT ENAMEL

Two-component aliphatic polyurethane enamel with **excellent resistance to the outdoor environment** (high protection from UV rays). Forms a hard, waterproof film that is resistant to oils, salts and petrols. Particularly suitable for high-performance finishes on suitably primed metal, plastic or concrete substrates. Highly recommended as a finish in epoxy-polyurethane anti-corrosion systems.

SURFACES

Suitably prepared metal or plastic.

FINISH

Matt

MAIN CHARACTERISTICS

- Indoor/outdoor
- Good hardness
- High chemical resistance

APPLY



DRY

1-2 h.

RECOAT

12-24 h.

SPREAD RATE

11-15 m²/L.

DILUTE

Brush, roller up to 3% ORODIS 720.
 Spray gun up to 15% of ORODIS 720

CLEAN WITH

ORODIS 720

MIX (4:1 by vol.)

Base

4L. 20L.

Catalyst OROCAT 714

1L. 5L.

COLOUR CHART



Grey RAL 7040



White

For other colours, please check.



POLYURETHANE

4L. / 20L.

2u. -



POLYURETHANE

4L. / 20L.

2u. -

OROMEL 612

POLYURETHANE SATIN ENAMEL

Two-component aliphatic polyurethane enamel with **excellent outdoor resistance** (high protection from UV rays). Forms a hard, waterproof film that is resistant to oils, salts and petrols. Particularly suitable for high-performance finishes on suitably primed metal, plastic or concrete substrates. Highly recommended as a finish in epoxy-polyurethane anti-corrosion systems.

SURFACES

Suitably prepared metal or plastic.

FINISH

Satin

MAIN CHARACTERISTICS

Indoor/outdoor Good hardness

High chemical resistance

APPLY 9-11 m ² /L.	DRY 1-2 h.	FORCED DRYING 10-15 min. at 20°C and then 20-30 min. at 70-80°C	RECOAT 12-24 h.
SPREAD RATE 9-11 m ² /L.	DILUTE Brush, roller up to 3% ORODIS 720 Spray gun up to 15% ORODIS 720	CLEAN WITH ORODIS 720	

MIX (4:1 by vol.)

Base 4L. 20L.
Catalyst OROCAT 714 1L. 5L.

COLOUR CHART

Grey RAL 7040 White



For other colours, please check.

OROMEL 614

POLYURETHANE GLOSS ENAMEL

Two-component aliphatic polyurethane enamel with **excellent outdoor resistance** (high protection from UV rays). Forms a hard, waterproof film that is resistant to oils, salts and petrols. Particularly suitable for high-performance finishes on suitably primed metal, plastic and concrete substrates. Validated by CIDETEC for C3-C5 systems.

SURFACES

Suitably prepared metal or plastic.

FINISH

Gloss

MAIN CHARACTERISTICS

Indoor/outdoor Good hardness

High chemical resistance

APPLY 9-11 m ² /L.	DRY 1-2 h.	RECOAT 12-24 h.
SPREAD RATE 9-11 m ² /L.	DILUTE Brush, roller up to 3% ORODIS 720 Spray gun up to 15% ORODIS 720	CLEAN WITH ORODIS 720

MIX (4:1 by vol.)


Base 4L. 20L.
Catalyst OROCAT 714 1L. 5L.

COLOUR CHART

Grey RAL 7040 White



For other colours, please check.



ÉPOXY

4KG. / 20KG.

2u. -



ÉPOXY

4L. / 20L.

2u. -

OROMEL 634

WATER-BASED EPOXY GLOSS ENAMEL

Two-component water-based epoxy enamel. Formulated with polymeric emulsions for quick drying and excellent curing reaction up to temperatures of 10°C. Excellent mechanical properties, high chemical resistance and easy cleaning. Allows thicknesses over 100 microns to be applied. Solvent-free, it is recommended for use in schools, health centres, food industries, etc.

SURFACES

Metal, concrete and cement.

FINISH

Gloss

MAIN CHARACTERISTICS

- Indoor
- Good hardness
- Odourless
- Good levelling
- High impermeability

APPLY 	TOUCH DRY 2-3 h.	TOTAL DRY 7 days	RECOAT 8-48 h.
SPREAD RATE 6-8 m ² /Kg.	DILUTE Brush and roller up to 10% of water 1 st coat. Spray gun up to 10% water	CLEAN WITH Water	

MIX (4:1 by weight)

Base 4Kg. 20Kg.
Catalyst OROCAT 734 1Kg. 5Kg.

COLOUR CHART

Grey RAL 7040 White

For other colours, please check.

OROMEL 644

SOLVENT-BASED EPOXY ENAMEL

Two-component, polyamide epoxy resin-based enamel with **high gloss** and high resistance to chemicals, fats, oils and petrols. Excellent hardness and resistance to abrasion and wear. Especially recommended for painting metal structures, machinery, or tools requiring high physical and chemical resistance. Indoor product.

SURFACES

Metal, concrete and cement.

FINISH

Gloss

MAIN CHARACTERISTICS

- Indoor
- Good hardness
- High chemical resistance

APPLY 	DRY 4 h.	FORCED DRYING 30 min. (T=100°C)	RECOAT 24-48 h.
SPREAD RATE 12-15 m ² /L.	DILUTE Brush and roller up to 15% of ORODIS 718. Spray gun: up to 20% Airless gun up to 10%		CLEAN WITH ORODIS 718

MIX (2:1 by vol.)

Base 4L. 20L.
Catalyst OROCAT 744 2L. 4L.

COLOUR CHART

Grey RAL 7040 White

For other colours, please check.



ÉPOXY

2L.

2u.



OROMEL 649

FOOD-SAFE EPOXY ENAMEL

High thickness coating based on epoxy resins. Two-component product for indoor use. Superior hardness and **absolute washability** with water and detergents.

Solvent-free. Withstands continuous temperatures up to 80°C. Food-safe certificate.

SURFACES


Iron and concrete.

FINISH

Gloss

MAIN CHARACTERISTICS

 Indoor

 Good hardness

APPLY




DRY

 7-9 h.

RECOAT

 24 h.

SPREAD RATE

 6-8 m²/L.

DILUTE

Not diluted

CLEAN WITH

 ORODIS 718

MIX (2:1 by vol.)

Base

Catalyst OROCAT 749

 2L.

 1L.

COLOUR CHART

 Grey RAL 7040

 White



For other colours, please check.

Fireproof paints



FIREPROOF PAINTS

OROFIRE 651: Water-based intumescent paint 60 min

OROFIRE 680: Flame-retardant paint



ACRYLIC

25KG.



-



CHLORINATED RUBBER

4L. / 20L.



-



OROFIRE 651

WATER-BASED INTUMESCENT PAINT - 60 MIN.

Water-based intumescent paint, recommended for passive fire protection of metal structures in construction. In contact with the flame, the paint swells to form a foam that slows down the heating of pillars and beams while maintaining their load-bearing capacity. **High efficiency at low thickness.** CE marking.

SURFACES

Steel.

FINISH

Matt

MAIN CHARACTERISTICS



Indoor

APPLY



DRY

4-6 h.

RECOAT

24 h.

SPREAD RATE

Please check

DILUTE

Up to 5% water

CLEAN WITH

Water

COLOUR CHART



White



OROFIRE 680

FLAME-RETARDANT PAINT

Flame-retardant paint based on chlorinated rubber resins. Emits non-combustible gases that prevent flame propagation through the film of paint. Does not extinguish fires of other materials. Not resistant to plant oils. Especially suitable for all indoor elements that require passive fire protection: metal structures, corridors, warehouses, etc. **Certificate B-s1,d0.**

SURFACES

Cement, concrete and iron.

FINISH

Semi-mate

MAIN CHARACTERISTICS



Indoor



Fireproof paint



High adhesion



High chemical resistance

APPLY



DRY

30-60 min.

RECOAT

8-12 h.

SPREAD RATE

7-8 m²/L.

DILUTE

Up to 15% of ORODIS 719 1st coat

CLEAN WITH

ORODIS 719

COLOUR CHART



Colourless White

For other colours, please check.

Pigment pastes



PIGMENT PASTES

OROCOLOR 926

PIGMENT PASTE 9700



1L.
6u.



1KG.
6u.

OROCOLOR 926

PIGMENT PASTES COLTEC

Range of pigment pastes, highly compatible with a wide variety of products (water-based and synthetic), both indoor and outdoor. **High stability.** Their high quality, excellent resistance and careful viscosity allow use in colour mixing systems with different types of bases, ensuring a wide range of lead-free colours.

MAIN CHARACTERISTICS

 High compatibility

COLOUR CHART



PIGMENT PASTES 9700


PIGMENT PASTES PINLAK

Range of pigment pastes, highly compatible with a wide variety of industrial products such as quick-drying enamels, chlorinated rubbers, polyurethanes and epoxies. Manufactured with high quality pigments and resistance to the outdoor environment. The excellent fluidity of the pastes makes them an ideal product for use in industrial colour mixing systems, guaranteeing a wide range of colours. **High colour fastness.**

MAIN CHARACTERISTICS

 High compatibility

COLOUR CHART





ORODIS 713

CLEANING SOLVENT

Quick-evaporating solvent with high solubility power, designed for cleaning utensils and tools.

ORODIS 715

SOLVENT OROCLASSIC

Odourless solvent, designed exclusively for cleaning and diluting **OROCLASSIC 25**.

ORODIS 716

SYNTHETIC AND CHLORINATED RUBBER S/R SOLVENT

Quick-drying aromatic solvent, designed especially for use in industrial paints.

ORODIS 717

SOLVENT FOR GUNS

Solvent designed especially for diluting in sprayed and hammertone paints.

ORODIS 718

OVEN/EPOXY SOLVENT

Solvent designed especially for two-component epoxy paints.

ORODIS 719

SYNTHETIC AND CHLORINATED RUBBER SOLVENT

Solvent designed especially for diluting, or for cleaning synthetic and chlorinated rubber paints.

ORODIS 720

POLYURETHANE SOLVENT

Solvent designed especially for two-component polyurethane paints.

ORODIS 721

LACQUER SOLVENT NITRO

Solvent designed especially for quick-drying lacquers.

ORODIS 723

AROMATIC SOLVENT

Solvent formulated as a substitute for turpentine, suitable for synthetic paints.


ORODIS 726

SOLVENT WASH PRIMER

High-polarity solvent, designed especially for wash primers and shop primers.

SOLVENT PACKS:

 1L. / 5L. / 20L.

 6u. 2u. -



Applied with brush



Applied with roller



Applied with gun



Applied with airless



Applied with trowel



Applied with spiked roller



Water-based



Solvent-based



Pack sizes



Box capacity



Catalyst



Kolare. Colour mixing system



Warranty seals



CE Certificate



Ecolabel Certificate



Fire rating certificate



Ecological product



Certified UNE EN 71-3



A+ Indoor air emissions



Food-safe certificate

COLOUR CHART

The colours shown in the colour charts throughout the catalogue are for guidance only, and differ from the actual colours due to the limitations of printing systems. We recommend checking actual colours at the points of sale.



FIRE RATING CERTIFICATE

All products that have some kind of inflammable material have to pass a series of experimental tests. After passing the tests, the products are classified on a scale of values that indicate the inflammability level of the material.

Standard UNE-EN 13501 sets out the Euroclasses in which the materials used for construction are classified. It also classifies inflammable products according to their production of smoke and toxic particles. There are therefore three scales to classify smoke production (s1, s2 and s3), and another three to classify the particles (d0, d1 and d2). Below is the UNE-EN 13501 Standard classification for fire resistance of products for construction materials (walls and ceilings):

CLASSIFICATION FOR WALLS AND CEILINGS. ACCORDING TO STANDARD UNE-EN 13501-1

- A1 Non-combustible. No contribution to fire
- A2 Non-combustible. No contribution to fire
- B Combustible. Very limited contribution to fire
- C Combustible. Limited contribution to fire
- D Combustible. Medium contribution to fire
- E Combustible. High contribution to fire
- F Unclassified. Unspecified performance

ADDITIONAL SMOKE OPACITY INDICES

- s1 Little or no smoke
- s2 Quite a lot of smoke
- s3 Substantial smoke

ADDITIONAL FLAME

DROPLETS/PARTICLES INDEX

- d0 No flaming droplets/particles
- d1 Some flaming droplets/particles
- d2 Flaming droplets/particles



A+ INDOOR AIR EMISSIONS

According to Decree n° 2011-321 of the Official Journal of France, labelling of construction products is mandatory since 1st September 2013. The stated aim is to encourage the use of low-emission construction materials.

The regulatory label relates to the performance of products in terms of VOC emissions in the air inside a building. These emissions are measured 28 days after installation, application or incorporation in a room.

There are 4 classes in accordance with performance, ranging from A+ for products with very little or no VOC, to C for products considered to have high emissions. Decree n° 2011-321 does not in any way affect the obligation to withdraw Class C products from the market.

This VOC label refers to construction materials. The products referred to in the regulation are those intended, whether exclusively or not, for indoor use:

- Floor, wall or ceiling coatings.
- Partition walls and suspended ceilings.
- Insulating products.
- Doors and windows.
- Products intended for placing or preparing the aforementioned products.

Volatile organic compounds are emitted by many products, such as:

- Fuel.
- Household cleaners, disinfectants, cosmetics, degreasers.
- Construction materials.
- Furniture.
- Paint, varnish, lacquers.
- Sealants and adhesives.



ECOLABEL CERTIFICATE

The Ecolabel is also known as the European Ecolabel. This is a voluntary scheme that aims to help European consumers to easily identify products that are green and environmentally friendly. Ecolabel is only awarded to those products or services that meet the necessary requirements in accordance with a series of studies carried out by the EUEB (European Union Eco-Labeling Board). Only products that strive to reduce pollution and energy consumption are awarded the Ecolabel. The Ecolabel is also a guarantee that the product or service purchased is high quality and meets stringent environmental criteria.

What does the Ecolabel mean?

The Ecolabel certificate for paint guarantees that it is a product with less atmospheric contamination and low VOCs (volatile organic compounds), and that it is not aggressive to your health and the environment.

Furthermore, the label represents less energy expenditure in producing the paint. It also means use of recycled fibres or sustainable forests.



UNE-EN 71-3:2013 Toy safety

Coatings used in toys, cradles, children's furniture, etc., are often subject to studies on migration of metals based on Standard UNE-EN 71-3, which simulates the extraction that may exist when a baby sucks on these products.

Standard UNE-EN 71-3 sets out the requirements and test methods for the migration of a group of metals that may be present in the materials of toys or furniture, and that are susceptible to being sucked, bitten or ingested by the child. This standard sets out the risks derived from the general tendency of babies and young children to put everything in their mouths, which brings an increase in the possibilities of migrating and absorbing certain chemical elements that are part of the product.

This standard focuses on the chemical conditions that allow the different agents involved in marketing toys to meet the obligations of the Community Directive on toy safety (2009/48/EC)..



CE CERTIFICATE

Many products are required to bear the CE mark in order to be sold in the EU, showing that the manufacturer has assessed the product and that it is deemed to comply with all EU safety, health and environmental protection requirements. The CE marking is mandatory for products manufactured anywhere in the world that are to be marketed in the EU.

When is CE marking mandatory?

The CE marking is only mandatory for certain products for which there is an EU specification and where CE marking is required.



FOOD-SAFE CERTIFICATE

Legislation requires the manufacturer to provide a Declaration of Conformity for a paint or varnish suitable for direct contact with food and drink. The documentation required for marketing must include at least the manufacturer's health registration, the standards the product complies with, official tests of the paint or varnish (global migrations, specific migrations, organoleptic tests, physical and chemical resistance, etc.), and also indicate which food group it is suitable for. All this information allows authorities and customers to verify that both the product and the manufacturer meet all the requirements.



IRURENAGROUP

www.irurenagroup.com

Ctra. de Tolosa, s/nº. Apartado 30
20730 Azpeitia. Gipuzkoa. Spain

T: +34 943 157 099
F: +34 943 810 911