

Sayerlack is a brand of
SHERWIN-WILLIAMS

SAYERLACK S.r.l. - With a Single Shareholder

Via del Fiffò, 12 - 40065 Pianoro (BO) - Italia - C.P. 18
 tel. +39 051 770511 - fax +39 051 777437
 www.sayerlack.it - www.lineablavernici.it

Cod. Fisc. e Reg. Impr. Bo 08866930152 - P. IVA: IT 00494251200
 R.E.A. n. 313180 - Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531

Company under the direction and coordination of The Sherwin-Williams Company, USA

Technical Data Sheet

IF0425/XX
GOLD-O-LUX: GOLD PAINT

Supersedes previous issue dated 02/04/07

DATE 09-07-08

Colours:	00 clear	34 Naples gold
	35 Vesuvius gold	36 chrome silver
	37 bronze gold	38 antique gold
	73 silver	
Area of use:	Picture frames, furniture accessories.	
Method of use:	Spray	

Technical characteristics

Solids content (%):	col. 00, 73	11 ± 2
	col. 34, 35, 38	24 ± 2
	col 36	8 ± 1
	col. 37	20 ± 2
Specific gravity (kg/l):	col. 00	0.900 ± 0.030
	col. 34, 35	1.100 ± 0.030
	col. 36, 73	0.930 ± 0.030
	col. 37	1.030 ± 0.030
	col. 38	1.050 ± 0.030
Viscosity (DIN 4 at 20°C):	11" ± 1"	

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.

Sayerlack is a brand of
SHERWIN-WILLIAMS

SAYERLACK S.r.l. - With a Single Shareholder

Via del Fiffò, 12 - 40065 Pianoro (BO) - Italia - C.P. 18
tel. +39 051 770511 - fax +39 051 777437
www.sayerlack.it - www.lineablavernici.it

Cod. Fisc. e Reg. Impr. Bo 08866930152 - P. IVA: IT 00494251200
R.E.A. n. 313180 - Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531
Company under the direction and coordination of The Sherwin-Williams Company, USA

Shelf-life:

If the product is properly stored, shelf-life is unlimited.

After long periods of storage, always check homogeneity and stir well before use to eliminate any possible sediment.

Substrate preparation

Properly sanded polyurethane or polyester basecoats.

General characteristics

IF0425/00 is a clear binder. It can be mixed with gold powder (XT6701/35, XT6701/38) or with aluminium powder (XT6701/36) and this mixture can be stored for many months without any colour change to brown or green.

The mixture is obtained by mixing 250 g of aluminium/gold powder with 750 g of IF0425/00.

If thinning is required, use a polyurethane thinner (e.g. DT1150/00).

IF0425/00 can also be used as a clear protective coating for gold leaf application; for this application, it should be thinned 1:1 to 1:2 with acetone.

The other products in the IF0425/XX series already contain metallic pigments reproducing different gold shades and are ready to use.

Warning

IF0425/XX must be overcoated with acrylic-polyurethane topcoats, as IF0425/XX themselves exhibit neither scratch resistance nor chemical-physical resistance.

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.
WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.