

Technical Data Sheet

A539

Fire Retardent Thinner

Supersedes previous issue dated 30/06/04
DATE 13/03/12

A fire retardant additive for polyurethane coatings - Crystal clear finish with no loss of clarity is obtained from the use of this product

Area of use:	All furniture, domestic and contract coating applications.
Method of use:	All spray and equipment types suitable for the polyurethane coating being used
Mixing procedure:	By volume (lt)
Part A	PU COATING 100
Part B (hardener)	PU Hardener As recommended
Thinner	A589 20
	Use of more than the recommended maximum level of A589 will result in a final finish much softer than normally obtained.

Technical Characteristics

Solids content (%):	30 ± 1
Specific gravity (kg/l):	0.974 ± 0.030

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.

Sayerlack is a brand of
SHERWIN-WILLIAMS

Sherwin-Williams UK Coatings Ltd
A1 Business Park - Knottingley - West Yorkshire - WF11 0BU - England
tel. +44 (0)1977 673363 - fax +44 (0)1977 673521
info@sayerlack.co.uk - www.sayerlack.co.uk
Technical Service: tel. +39 051 770770 - fax +39 051 770521
customerservice@sayerlack.it
Registered in England: 07148590
VAT REG No. GB 987 3607 68 - VAT REG No. IE 9741724H

General Characteristics

Temperature for use	20 °C	
Pot-life:	Same as PU Coating	
Recommended application weight (g/m ²):	Same as PU Coating	
Drying time (X g/m ² at X °C):	Dust free	Same as PU Coating
	Touch dry	Same as PU Coating
	Stackable	Same as PU Coating
Number of coats:	Same as PU Coating	
Shelf-life:	12 Months Stored in sealed containers under normal warehouse conditions.	
Clean-up	DX1130	

Read the separate Health and Safety sheet prior to use. This is just one of a wide range of industrial wood coatings from Sherwin Williams. Should you require any further information on this, or any other product within our range, simply contact us at the address below.

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.