

Technical Data Sheet

WZG54/00**
FAST DRY AC LACQUER

DATE 22/10/12

Description of product

A Fast drying two pack solvent borne lacquer for most types of wood.
 Low formaldehyde emission during application, drying and from the dried film.
 After adding hardener the lacquer is ready for use undiluted.

Versions:	WZG5410: 10 gloss. WZG5425: 25 gloss. WZG5450: 50 gloss.
Area of use:	Suitable for fast production lines. For application onto vertical surfaces without the risk of sagging.
Method of use:	All spray types.
Mixing procedure:	By Volume (L)
Part A	WZG5400 10
Part B (hardener)	P088 1
Thinner	DSG27 Normally not required

Technical Characteristics

Solids content (%):	46 ± 1
Specific gravity (kg/l):	0.990 ± 0.030
Viscosity (B4 at 23°C):	WZG5400: 55-50"

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.

Sayerlack is a brand of
SHERWIN-WILLIAMS

Sherwin-Williams UK Coatings Ltd
A1 Business Park - Knottingley - West Yorkshire - WF11 0BU - England
tel. +44 (0)1977 673363 - fax +44 (0)1977 673521
info@sayerlack.co.uk - www.sayerlack.co.uk
Technical Service: tel. +39 051 770770 - fax +39 051 770521
customerservice@sayerlack.it
Registered in England: 07148590
VAT REG No. GB 987 3607 68 - VAT REG No. IE 9741724H

General Characteristics

Temperature for use	15-20°C	
Pot-life:	24 hours	
Recommended application weight (g/m ²):	Minimum 80, maximum 120	
Drying time (100g/m ² at 20°C):	Stackable	4-6 hours
Forced air drying: (100g/m ² at 70°C):	Stackable	30-40 mins
Number of coats:	Maximum 3	
Shelf-life:	1 Year	

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.